

BIOSYNTHESIS OF METAL NANOPARTICLES AND THEIR APPLICATIONS IN THE FIELD OF AGRICULTURE AND BIOMEDICAL SCIENCES

Abstract

The biosynthesis of metal nanoparticles has emerged as a sustainable and environmentally friendly approach, that offers unique advantages over conventional chemical synthesis methods. This procedure converts the metal ions into nanoparticles by using biological elements like plants, bacteria, fungi and enzymes. The resultant nanoparticles have unique features and have a wide range of uses in industries including agriculture and the biological sciences. These green synthesis techniques are appealing for agricultural applications because they are low cost-effective and environmentally friendly. The use of agro nanotechnology, which has applications from better food quality to reducing agricultural inputs, may significantly enhance crop productivity. Innovative methods like the detection and treatment of illness, the delivery of nano pesticides, the use of biopesticides and green pesticides, the gradual and continuous release of micronutrients, and fertilizers, etc. may be made possible by nanotechnology for the agro-food industry. Nanoparticles are attracting a lot of interest in biological sciences because of their unique features and adaptability. They are employed in a variety of applications like as drug delivery, cancer treatment, gene therapy, and antimicrobial protection.

Keywords: Nanotechnology, Fungi, Nanoparticles, Biosynthesis, Pesticides, Drug delivery.

Authors

Sharda Suman

M. Sc
Microbiology Department
Padmashree Institute of Management & Sciences, Kommagatta, Kengeri, Bengaluru
Karnataka, India.
jhasharda2902@gmail.com

Manjunathan C

M. Sc
Microbiology Department
Padmashree Institute of Management & Sciences, Kommagatta, Kengeri, Bengaluru
Karnataka, India.
cmanjunathan161@gmail.com

Dr. Sumanth B

Assistant Professor
Department of Microbiology
Padmashree Institute of Management & Sciences, Kommagatta, Kengeri, Bengaluru
Karnataka, India.
sumanthmscmb@gmail.com

I. INTRODUCTION

The process of creating nanoparticles by utilizing biological agents, such as plants, bacteria, fungi, algae, or other biomolecules, is known as "biosynthesis of nanoparticles" [1]. Compared to conventional chemical and physical methods, this green synthesis strategy has several benefits, such as cost-effectiveness, the capacity to customize the characteristics of nanoparticles for particular applications, and environmental friendliness. Nanoparticle biogenesis has been investigated in a variety of biological systems [2]. A variety of bioactive substances, including polyphenols, flavonoids, and terpenoids, are present in plant extracts, particularly those from the leaves, stems, and roots. These substances are good reducing and stabilizing agents for nanoparticles. The reduction and stabilization processes are made easier by the enzymes and proteins that microorganisms like bacteria and fungi have. Algae and other biological agents have further demonstrated potential for nanoparticle production [3]. The synthesis of nanoparticles is in great demand nowadays as nanotechnology has emerged as a game-changing field with extensive applications in several sectors. The biosynthesis of nanoparticles and their potential use in agriculture is one of the most exciting and quickly developing fields of nanotechnology [4]. It is possible to increase nutrient absorption efficiency and decrease waste by the regulated and targeted administration of agrochemicals, such as fertilizers and pesticides, through nanocarriers, that can increase crop yield and minimize environmental pollution [5].

II. NANOPARTICLES

Nanoparticles are extremely small particles that generally vary in size from 1 to 100 nanometres (1 nanometre is equivalent to one billionth of a meter). Since they are so little, they display special traits and behaviors that set them apart from their bulk counterparts. Nanoparticles can be synthesized from various materials, such as metals, metal oxides, polymers, and carbon-based materials [6].

Nanoparticles are referred to as being "biosynthesized" when microorganisms extract target ions from their environment and change those metal ions into the element metal utilizing enzymes created by cell processes [7]. Production may be classified as intracellular or extracellular depending on where nanoparticles are produced. Delivering ions within the microbial cell, where they mix with enzymes to generate nanoparticles, is the intracellular strategy [8]. Nanoparticles are created extracellularly by trapping reducing ions in the presence of enzymes and metal ions on cell surfaces. The biosynthesized nanoparticles have been applied in a wide range of sectors covering biosensors, speeding reaction speeds, separation research, cancer treatment, gene therapy, targeted medicine administration, agriculture, pharmaceutical carriers, DNA analysis, antimicrobial compounds, and MRI [9]. Since the beginning of life on Earth, inorganic substances and biological ones have been interacting constantly.

This continuous interaction made it possible for life to coexist with a well-organized mineral deposit on this planet [10]. Numerous bacteria can create inorganic nanoparticles via extracellular or intracellular pathways. This section covers the categories of oxide nanoparticles made up of magnetic and nonmagnetic oxide nanoparticles, sulfide nanoparticles, and other ad hoc nanoparticles [11]. It also discusses the synthesis of various nanoparticles via biological processes. The topic also includes metallic nanoparticles like

gold, silver, alloy, and other metal nanoparticles [12]. Fungi may be utilized to make a variety of nanoparticles, which include gold, silver, zinc oxide, and others [13]. Nanoparticles have been utilized since the fourth century. These are of enormous scientific interest because they serve a significant role in acting as the connecting link between the bulk materials, and atomic, or molecular structures [14].

The biogenesis of nanoparticles includes two important categories. The first process is called "Bioreduction" (in which metal ions are chemically reduced by living things into more stable forms), while the second is called "Biosorption" (in which nanoparticles from the environment adhere to living things) [15]. Numerous creatures with the potential to produce nanoparticles have not yet been fully investigated. In this work, we are aiming to identify fungi that can produce these nanoparticles as well as how to characterize them.

1. Trends for Formulation of Nanoparticles: There are two important trends in nanoparticle production [16]. these are the following: -

- **Top-Down Approach:** In a top-down technique, a bulk material is sliced into smaller and smaller pieces until a nano-sized particle is obtained. Typically, this approach is used in the physical production of nanoparticles [17].
- **Bottom-Up App Approach:** In the bottom-up technique, the substance is built up from the bottom up, or "bottom up." The creation of clusters or molecules as a result of atom-by-atom deposition results in the production of clustered monolayers on the surface of the substrate. It is usually done using chemical and biological methods [18].

2. Methods used for Nanoparticle Fabrication

- **Physical Methods:** The nanoparticles are synthesized using physical or mechanical processes referred to as physical methods. Some of the important procedures include mechanical ball milling, vapor condensation, thermal decomposition, arc discharge, photo irradiation, laser ablation, ultrasonication etc [19].
- **Chemical Methods:** The production of nanoparticles by the action of various chemical processes is referred to as chemical methods. Some of the chemical methods include a sol-gel method, solvothermal process, electrochemical process, sonochemical process, thermal plasma synthesis etc [20].
- **Biological Method:** "Biosynthesis of nanoparticles" refers to the method of making nanoparticles with biomedical applications that utilize microbes and plants. This approach is cost-effective, secure, compatible with biological systems, environmentally friendly, and secure [21]. The term "green synthesis" refers to synthesis that involves the use of plants, bacteria, fungi, algae, etc. They make it possible to produce industrial-scale, large quantities of pure ZnO NPs [22]. When NPs are produced via a biomimetic method, which also lessens the requirement for costly and hazardous chemicals, more catalytic activity may be seen [23]. The biogenic enzymatic method is preferred in comparison to chemical methods in

several aspects for producing nanoparticles. Although the latter methods may quickly create huge quantities of nanoparticles with certain sizes and shapes, they are challenging, antiquated, costly, and ineffectual, and they produce dangerous toxic wastes that are terrible for the environment as well as human health [24]. Enzymatic processes reduce the need for pricey chemicals, and the more socially acceptable "green" alternative uses less energy and is better for the environment.

III. METHODOLOGY

There are so many methods for the biosynthesis of nanoparticles. Here we have preferred the biosynthesis of nanoparticles using fungi. Soil samples have been collected from the mining area. The soil present in mining areas is capable of degrading more variety of metals so it can be used for various metal degradation [25]. Isolation of fungi by serial dilution method has been performed. For this, take 1 g of soil, weigh it, should be added to a test tube with 10 ml of distilled water, and thoroughly mix. Prepare five test tubes with a 9 ml capacity each for distilled water. Take 1/11 of a ml of Stoke into the first tube for the initial dilution. Take 1 ml of the first dilution once more and add it to the second tube, which will contain the second dilution. For the remaining three test tubes, which will represent the third, fourth, and fifth dilutions, repeat this procedure. Now Place 1 ml of each filtrate dilution in a Petri plate, add the culture media, and then tilt the dish to evenly distribute the sample and media [26]. Perform the identification of fungi by morphology and molecular method. The morphospecies of fungi will initially be determined from their cultures. Depending on their capacity for sporulation, the selected cultures are injected into various mediums. On PDA (Potato dextrose agar) containing Petri plates, the isolates are inoculated and incubated at $24\pm 2^{\circ}\text{C}$ for around one week. Lactophenol cotton blue staining is used to identify fungi growing out of the explants when they are in the sporulation stage. In the molecular method, for acquiring the fresh mycelia for DNA extraction, liquid cultures of fungal isolates are created using 50 mL of Potato Dextrose Broth medium (Hi Media, pH 7.3) in 100 mL Erlenmeyer flasks. Centrifugation at 8,000 rpm and 40°C for 10 min is used to separate the mycelia. Mycelia are gathered and physically crushed in liquid nitrogen. From 100 mg of fungus mycelia, genomic DNA is isolated [27]. Screening of potential fungi for nanoparticle production has been done once the identification is done. Screening is the process of choosing and assessing various fungal species according to how well and quickly they can synthesize nanoparticles. This screening procedure helps in the discovery of fungi that might be good candidates for the manufacture of green nanoparticles [28]. Now metal nanoparticles from the fungi have been synthesized. 1 g of metal hexahydrate was dissolved in 2–10 mL of fungal extract. After being extensively swirled with the use of a magnetic stirrer and kept in a pre-heated muffle furnace maintained at $400\pm 10^{\circ}\text{C}$ for two hours, the completed product was then further calcined at 700°C . So, it was also necessary to undertake a structural study on the synthesized metal NPs [29]. The size and architectures of the metal nanoparticles determine how much energy is required for the nucleation and growth of a supersaturated arrangement throughout various processes including coarsening, focused connection, and accumulation. Lastly, the Purification and characterization of metal nanoparticles by spectroscopic and microscopic methods (UV-visible spectroscopy, SEM, TEM, XRD) has been done. In a conventional UV-Vis spectrophotometer, one-half of a light beam is sent through a transparent cell holding a solution of the material being tested, and the other half is directed through a cell that is similar to the sample cell but contains the solvent instead of the substance. The device is designed to travel throughout the required wavelength

range, allowing comparison of the intensity of the two beams [30]. If the substance absorbs light of a specific wavelength, the intensity of the sample beam (IS) will be lower than the intensity of the reference beam. SEM (Scanning electron microscopy) is used to examine the surface morphology of the synthesized nanoparticles (NPs). Through the use of dynamic light scattering (DLS), the size distribution of the synthesized NPs is determined. TEM (Transmission electron microscopy) is used to determine the size of synthesized metal nanoparticles [31].




Figure 1: Schematic Representation of Applications of Metallic Nanoparticles

Table 1: Tabular Representation of Organisms, NPs Extracted, and Applications

Organism	NPs Extracted	Applications	References
<i>Aspergillus nidulans</i>	Zinc oxide	Used as an antioxidant, Used for drug delivery agents	[32]
<i>Aspergillus fumigatus</i> , <i>Aspergillus niger</i>	Silver oxide	Can be used to prevent HIV from binding to host cells	[33]
<i>Fusarium oxysporum</i>	Barium titanate	Enhances the germination of old spinach and wheat seeds	[34] [35]
<i>Penicillium chrysogenum</i>	Copper oxide	Wound healing, antioxidant Nanofertilizers, used to detect fungus infestation	[36],[37]
<i>Aspergillus japonicus</i>	Iron oxide	Can be used as MRI contrast agents	[38],[39]
<i>Talaromyces purpureogenus</i>	Gold oxide	Can be used for molecular imaging of various enzymatic and metabolic activities	[40]

IV. APPLICATIONS

Due to their distinctive characteristics and variety of capabilities, metal nanoparticles have a wide range of applications in a variety of sectors. Fig 1. Shows some of the applications of nanoparticles of metal nanoparticles in various fields.

1. Agricultural Applications

- **Nanoparticle's Interaction with the Plants:** The agricultural industry benefits from advances in science and technology, which provide us with fresh ideas and solutions to difficult issues. With the development of nanotechnology, more effective and contaminant-free nanoformulations for sustainable agriculture are constantly being developed [41]. These novel compounds can affect plant physiology immediately after entering the complicated plant-soil system, which may be easily exploited to understand the consequences. Furthermore, crucial information on the interaction of these NPs with plants, whether positive or negative, is necessary for the regulated delivery of active chemicals. As a result, they may open up new opportunities for manufacturing superior nanomaterial-based goods. It is also thought that the concentration of NPs in the natural environment is substantially lower than levels considered harmful [42].
 - Size-dependent uptake of NPs
 - Surface Charge-Dependent Uptake of NPs
 - Anatomical Difference and Mode of Application-Related NP Uptake
 - Methods to Study Uptake, Quantification, and Translocation of NPs
- **NPs for Plant Growth and Seed Germination:** The absorption of NPs within plants is heavily influenced by the size, chemical content, and functional groups on their surface, as well as the kind of coating. The interaction and absorption of NPs cause molecular changes that alter plant physiology overall. The potential impact of multi-walled carbon nanotubes (MWCNTs) on tobacco cell development (55-64% increase) is due to a novel molecular mechanism. The bulk of the genes that have been activated are involved in cell division (CycB), cell wall expansion (NtLRX1), and tobacco aquaporin (NtPIP1) [43]. The capacity of NMs to penetrate the hard layer of seeds and enable water importation determines improved development and vigor. Furthermore, the seed priming technique using nanotechnology is a promising strategy; before planting, it confirms the potential of high-yield value crops [44]. The use of MWCNTs has an impact on the development of various essential crops, including barley, soybeans, and maize. Raman spectroscopy and TEM imaging demonstrated that MWCNTs congregate inside the endosperm of exposed seeds. The nanoparticles were delivered to various regions of the plant and interacted with cellular machinery, boosting plant development. Mesoporous silica nanoparticles (MSNs) can promote photosynthesis by interacting with chloroplasts, resulting in higher seed germination, total protein, and chlorophyll content [45]. MSNs at the greatest concentration (2,000 mg/l) did not cause stress in any of the plants, indicating a safer application as a smart delivery method [46].

2. Role in Biomedical Sciences

- **Drug Delivery:** Drug transfer to particular places is important in biological and medical science because it allows medications to be delivered to the desired spot while avoiding injury to normal cells in the surrounding environment. Biological components such as carbohydrates, protein, phenols, receptors, and medicines might be coupled with endophytic fungal-generated silver-zinc oxide NPs via surface alternation of green-produced nanoparticles. This alternative describes a specific role of bio nano assembles that allows them to be used in medicine for specific medication delivery [47]. As a result, it is appropriate to precisely target tumor cells using endocytosis, a lively targeting approach. Similarly, the outer surface of green processed nanomaterials is surrounded by biological chemicals derived from plant extract, which may be transmitted. Meanwhile, bimetallic nanoparticles are known for their exceptional assembly capability due to their enhanced surface area, which allows them to bond with a wide range of chemical compounds such as biological molecules and medicines. Thus, plant-based metal nanoparticles may be taken up or function by fungal extract biomolecules, which can be used as a natural linker for drug delivery to the appropriate places [48]. The biostability of biosynthesized silver-zinc oxide bimetallic nanoparticles in healthy and diseased cells makes them more reliable as a drug delivery vector. The enhanced activity of the drug delivery system might be attributed to the bimetallic nanoparticles' extra targeted effects, greater penetrability, and retaining properties. Analyzing the biocompatibility of fungal-derived metal nanoparticles, it is simple to predict the utility of biologically produced manufactured metal NPs as a competent vehicle for cancer-targeted drug administration in the future [49].
- **Antioxidant use:** The fungal-derived metal NPs are being acknowledged for carrying antioxidant use as compared to metallic NPs. DPPH free radicals indicate antioxidant action depending upon quantity at an optimal concentration of synthesized NPs compared to ascorbate (standardized antioxidant anion). Additionally, the solution change of color is due to the NPs observed. Researchers showed that the combination of silver with zinc oxide forming plant-based nanomaterials increases their antioxidant capacity and their anti-proliferative behavior causes the elimination of free radicals [50]. Metal NPs as an antioxidant agent could be additionally applicable against vital fights like liver problems and cancer. Certain metal nanoparticles, such as gold and silver nanoparticles, exhibit surface plasmon resonance (SPR), which involves the collective oscillation of electrons on the nanoparticle surface. This property has been explored for its potential to enhance the antioxidant activity of these nanoparticles [51]. Free radicals can be scavenged by metal nanoparticles, such copper, silver, and gold nanoparticles, because of their special surface characteristics. To assist in stopping oxidative damage to cells and tissues, they can provide electrons to neutralize free radicals. Antioxidant reactions can be accelerated by some metal nanoparticles because of their catalytic activity.[52]

Some metal nanoparticles possess magnetic properties. Antioxidants can be specifically delivered to parts of the body experiencing heightened oxidative stress by

employing external magnetic fields using these nanoparticles to those specific places [53].

The antioxidant capabilities of metal nanoparticles can be influenced by their size. Compared to their bulk counterparts, nanoparticles with sizes between one and one hundred nanometers frequently display distinctive physicochemical characteristics. Their interactions with cellular constituents and free radicals may be impacted by this size-dependent behavior [54].

- **Antimicrobial use:** The fungal-derived metal alloy nanoparticles were successfully described as an agent that inhibits microbial development by destroying it. When compared to monometallic nanoparticles, these alloy NPs demonstrated enhanced antibacterial activity. Because of their tiny size and photocatalytic capabilities, metal NPs have demonstrated action against *Micrococcus luteus* and *E. coli* [55]. Furthermore, the antibacterial activity of metal NPs against *Staphylococcus aureus*, *Pseudomonas aeruginosa*, *Bacillus subtilis*, and *Klebsiella pneumonia*. As a result, metal NPs were used among other nanomaterials to evaluate their impact on microorganisms [56]. These nanoparticles have shown significant effectiveness against infective gram-positive and gram-negative bacterial strains.




Figure 2: Other Applications of Nanoparticles

V. CONCLUSION

The synthesis of metallic nanoparticles with the help of fungi can be employed to make compacts utilizing a low-combustion method. Ultraviolet-visible spectroscopy, FT-IR, SEM with EDX, DLS, and TEM with SEAD will be used for the characterization of the produced nanopowder to show the production of the nanoparticles. This biosynthesis focuses

on the fungi-mediated synthesis of metallic nanoparticles in a simple and environmentally acceptable technique that is innovative, nontoxic, and cost-effective when compared to physical and chemical production. The green synthesis techniques provide several benefits over conventional chemical and physical procedures, including the use of plant extracts, microbes, fungi, or other biomolecules. Improved nutrient absorption efficiency, reduced waste, and reduced environmental effects are the results of the controlled and targeted dispersion of agrochemicals that use nanocarriers, including fertilizers and pesticides. Because of the increased demand from the application point of caution tests, large-scale research, and the development of vaccine and home-derived applications, fungal-derived synthesis can provide a valuable and monetary outlet for these NPs. As a result, manufacturing and changing fungal-generated metal NPs to cope with the potentials typically provided by chemically manufactured metal NPs are unquestionably necessary.

REFERENCES

- [1] Pandit, C., Roy, A., Ghotekar, S., Khusro, A., Islam, M. N., Emran, T. B., ... & Bradley, D. A. (2022). Biological agents for the synthesis of nanoparticles and their applications. *Journal of King Saud University-Science*, 34(3), 101869.
- [2] Samuel, M. S., Ravikumar, M., John J, A., Selvarajan, E., Patel, H., Chander, P. S., ... & Chandrasekar, N. (2022). A review on green synthesis of nanoparticles and their diverse biomedical and environmental applications. *Catalysts*, 12(5), 459.
- [3] Ishak, N. M., Kamarudin, S. K., & Timmiati, S. N. (2019). Green synthesis of metal and metal oxide nanoparticles via plant extracts: an overview. *Materials Research Express*, 6(11), 112004.
- [4] Enamala, Manoj Kumar, Bhulakshmi Kolapalli, P. Divya Sruthi, Silpi Sarkar, Chandrasekhar Kuppam, and Murthy Chavali. "Applications of nanomaterials and prospects for nanobionics." *Plant Nanobionics: Volume 2, Approaches in Nanoparticles, Biosynthesis, and Toxicity* (2019): 177-197.
- [5] Vasseghian, Y., Arunkumar, P., Joo, S. W., Gnanasekaran, L., Kamyab, H., Rajendran, S., ... & Klemeš, J. J. (2022). Metal-organic framework-enabled pesticides are an emerging tool for sustainable cleaner production and environmental hazard reduction. *Journal of Cleaner Production*, 133966.
- [6] Findik, F. (2021). Nanomaterials and their applications. *Periodicals of Engineering and Natural Sciences*, 9(3), 62-75.
- [7] Bahrulolum, H., Nooraei, S., Javanshir, N., Tarrahimofrad, H., Mirbagheri, V. S., Easton, A. J., & Ahmadian, G. (2021). Green synthesis of metal nanoparticles using microorganisms and their application in the agri-food sector. *Journal of Nanobiotechnology*, 19(1), 1-26.
- [8] Li, Xiangqian, et al. "Biosynthesis of nanoparticles by microorganisms and their applications." *Journal of nanomaterials* 2011 (2011): 1-16.
- [9] Ovais, M., Khalil, A. T., Ayaz, M., Ahmad, I., Nethi, S. K., & Mukherjee, S. (2018). Biosynthesis of metal nanoparticles via microbial enzymes: a mechanistic approach. *International journal of molecular sciences*, 19(12), 4100.
- [10] Cowen, Richard. *History of life*. John Wiley & Sons, 2013.
- [11] Singh, Anirudh, et al. "Green synthesis of metallic nanoparticles as effective alternatives to treat antibiotics resistant bacterial infections: A review." *Biotechnology Reports* 25 (2020): e00427.
- [12] Jamkhande, Prasad Govindrao, et al. "Metal nanoparticles synthesis: An overview on methods of preparation, advantages and disadvantages, and applications." *Journal of drug delivery science and technology* 53 (2019): 101174.
- [13] Król, A., et al. "Zinc oxide nanoparticles: Synthesis, antiseptic activity and toxicity mechanism." *Advances in colloid and interface science* 249 (2017): 37-52.
- [14] Thomas, J., Thomas, S., Kalarikkal, N., & Jose, J. (Eds.). (2018). *Nanoparticles in polymer systems for biomedical applications*. CRC Press.
- [15] El-Seedi, Hesham R., et al. "Metal nanoparticles fabricated by green chemistry using natural extracts: Biosynthesis, mechanisms, and applications." *RSC advances* 9.42 (2019): 24539-24559.
- [16] Biswas, Abhijit, et al. "Advances in top-down and bottom-up surface nanofabrication: Techniques, applications & prospects." *Advances in colloid and interface science* 170.1-2 (2012): 2-27.

- [17] Usman, Ken Aldren S., et al. "Downsizing metal–organic frameworks by bottom-up and top-down methods." *NPG Asia Materials* 12.1 (2020): 58.
- [18] Capek, Ignác. *Nanocomposite structures and dispersions*. Vol. 23. Elsevier, 2019.
- [19] Ghorbani, Hamid Reza. "A review of methods for synthesis of Al nanoparticles." *Orient. J. chem* 30.4 (2014): 1941-1949.
- [20] Rane, Ajay Vasudeo, et al. "Methods for synthesis of nanoparticles and fabrication of nanocomposites." *Synthesis of inorganic nanomaterials*. Woodhead Publishing, 2018. 121-139.
- [21] Jan, Hasnain, et al. "A detailed review on the biosynthesis of platinum nanoparticles (PtNPs), their potential antimicrobial and biomedical applications." *Journal of Saudi Chemical Society* 25.8 (2021): 101297.
- [22] Agarwal, H., Kumar, S. V., & Rajeshkumar, S. (2017). A review on green synthesis of zinc oxide nanoparticles—An eco-friendly approach. *Resource-Efficient Technologies*, 3(4), 406-413.
- [23] Sharma, D., Kanchi, S., & Bisetty, K. (2019). Biogenic synthesis of nanoparticles: a review. *Arabian journal of chemistry*, 12(8), 3576-3600.
- [24] Mughal, B., Zaidi, S. Z. J., Zhang, X., & Hassan, S. U. (2021). Biogenic nanoparticles: Synthesis, characterization, and applications. *Applied Sciences*, 11(6), 2598.
- [25] Saif, Sadia, Arifa Tahir, and Yongsheng Chen. "Green synthesis of iron nanoparticles and their environmental applications and implications." *Nanomaterials* 6.11 (2016): 209.
- [26] Ukpaka, C. (2016). Development of a model for bioremediation of crude oil using moringa extract. *Chem. Int*, 2(9).
- [27] Senanayake, I. C., et al. "Morphological approaches in studying fungi: Collection, examination, isolation, sporulation and preservation." *Mycosphere* 11.1 (2020): 2678-2754.
- [28] Flieger, Jolanta, et al. "Antioxidants: Classification, natural sources, activity/capacity measurements, and usefulness for the synthesis of nanoparticles." *Materials* 14.15 (2021): 4135.
- [29] Sumanth, Basavaraju, et al. "Mycogenic synthesis of extracellular zinc oxide nanoparticles from *Xylaria acuta* and its nanoantibiotic potential." *International Journal of Nanomedicine* (2020): 85198536.
- [30] Jayachandran, Ashwini, T. R. Aswathy, and Achuthsankar S. Nair. "Green synthesis and characterization of zinc oxide nanoparticles using *Cayratia pedata* leaf extract." *Biochemistry and Biophysics Report* 26 (2021): 100995.
- [31] Sumanth, Basavaraju, et al. "Fungal biogenesis of NPs and their limitations." *Microbial Nanotechnology: Green Synthesis and Applications* (2021): 81-101.
- [32] Khan, Shahid Ali, et al. "Fourier transform infrared spectroscopy: fundamentals and application in functional groups and nanomaterials characterization." *Handbook of materials characterization* (2018): 317-344.
- [33] Vijayanandan, A. S., & Balakrishnan, R. M. (2020). Photostability and electrical and magnetic properties of cobalt oxide nanoparticles through the biological mechanism of endophytic fungus *Aspergillus nidulans*. *Applied Physics A*, 126, 1-13.
- [34] Jaidev, L. R., and G. Narasimha. "Fungal mediated biosynthesis of silver nanoparticles, characterization and antimicrobial activity." *Colloids and surfaces B: Biointerfaces* 81.2 (2010): 430-433.
- [35] Khandel, Pramila, and Sushil Kumar Shahi. "Mycogenic nanoparticles and their bio-prospective applications: current status and future challenges." *Journal of Nanostructure in Chemistry* 8 (2018): 369-391.
- [36] Ali, Attarad, et al. "Synthesis, characterization, applications, and challenges of iron oxide nanoparticles." *Nanotechnology, science, and applications* (2016): 49-67.
- [37] Mohamed, Asem A., et al. "Eco-friendly mycogenic synthesis of ZnO and CuO nanoparticles for in vitro antibacterial, antibiofilm, and antifungal applications." *Biological trace element research* 199 (2021): 2788-2799.
- [38] Siddiqi, Khwaja Salahuddin, and Azamal Husen. "Current status of plant metabolite-based fabrication of copper/copper oxide nanoparticles and their applications: a review." *Biomaterials Research* 24.1 (2020): 1-15.
- [39] Bhargava, Arpit, et al. "Synthesis, characterization and mechanistic insights of mycogenic iron oxide nanoparticles." *Nanotechnology for sustainable development*. Springer International Publishing, 2014.
- [40] Ali, Attarad, et al. "Synthesis, characterization, applications, and challenges of iron oxide nanoparticles." *Nanotechnology, science, and applications* (2016): 49-67.
- [41] Hu, Xiaowen, et al. "Cytotoxicity of aptamer-conjugated chitosan encapsulated mycogenic gold nanoparticles in human lung cancer cells." *Journal of nanostructure in chemistry* (2021): 1-13.

- [42] Nagar, A., & Pradeep, T. (2020). Clean water through nanotechnology: needs, gaps, and fulfillment. *ACS nano*, 14(6), 6420-6435.
- [43] Saleem, H., & Zaidi, S. J. (2020). Developments in the application of nanomaterials for water treatment and their impact on the environment. *Nanomaterials*, 10(9), 1764.
- [44] Khodakovskaya, M. V., De Silva, K., Biris, A. S., Dervishi, E., & Villagarcia, H. (2012). Carbon nanotubes induce growth enhancement of tobacco cells. *ACS nano*, 6(3), 2128-2135.
- [45] Khodakovskaya, M. V., De Silva, K., Biris, A. S., Dervishi, E., & Villagarcia, H. (2012). Carbon nanotubes induce growth enhancement of tobacco cells. *ACS nano*, 6(3), 2128-2135.
- [46] Zhao, L., Lu, L., Wang, A., Zhang, H., Huang, M., Wu, H., ... & Ji, R. (2020). Nano-biotechnology in agriculture: use of nanomaterials to promote plant growth and stress tolerance. *Journal of agricultural and food chemistry*, 68(7), 1935-1947.
- [47] Robson, A. (2012). SERS-active peptide nanoparticles for investigating protein allostery and bionanoassembly.
- [48] Tavares, T. D., Antunes, J. C., Ferreira, F., & Felgueiras, H. P. (2020). Biofunctionalization of natural fiber-reinforced biocomposites for biomedical applications. *Biomolecules*, 10(1), 148.
- [49] Monika, P., Chandrababha, M. N., Hari Krishna, R., Vittal, M., Likhitha, C., Pooja, N., & Chaudhary, V. (2022). Recent advances in pomegranate peel extract mediated nanoparticles for clinical and biomedical applications. *Biotechnology and Genetic Engineering Reviews*, 1-29.
- [50] Jan, H., Shah, M., Andleeb, A., Faisal, S., Khattak, A., Rizwan, M., ... & Abbasi, B. H. (2021). Plant-based synthesis of zinc oxide nanoparticles (ZnO-NPs) using aqueous leaf extract of *aquilegia pubiflora*: their antiproliferative activity against HepG2 cells inducing reactive oxygen species and other in vitro properties. *Oxidative medicine and cellular longevity*, 2021.
- [51] Adrianto, Nanang, et al. "Localized surface plasmon resonance properties of green synthesized silver nanoparticles." *Nano-Structures & Nano-Objects* 31 (2022): 100895
- [52] Samrot, Antony V., et al. "Nanoparticles, a double-edged sword with oxidant as well as antioxidant properties—a review." *Oxygen* 2.4 (2022): 591-604
- [53] Sharma, Harshita, et al. "Metal nanoparticles: a theranostic nanotool against cancer." *Drug discovery today* 20.9 (2015): 1143-1151.
- [54] Fu, Peter P., et al. "Mechanisms of nanotoxicity: generation of reactive oxygen species." *Journal of food and drug analysis* 22.1 (2014): 64-75.
- [55] Chauhan, A., Verma, R., Kumari, S., Sharma, A., Shandilya, P., Li, X., ... & Kumar, R. (2020). Photocatalytic dye degradation and antimicrobial activities of Pure and Ag-doped ZnO using *Cannabis sativa* leaf extract. *Scientific reports*, 10(1), 1-16.
- [56] Motshekga, S. C., Ray, S. S., Onyango, M. S., & Momba, M. N. (2013). Microwave-assisted synthesis, characterization, and antibacterial activity of Ag/ZnO nanoparticles supported bentonite clay. *Journal of hazardous materials*, 262, 439-446.

