

Review on chitosan/copper composites as potential biocomposites for various applications

Anjaly Gopinadhan
Department of Chemistry
Christ College (Autonomous),
Irinjalakuda, Kerala, India
anjaly99gopinadhan@gmail.com

Meril Shelly
Department of Chemistry
Christ College (Autonomous),
Irinjalakuda, Kerala, India
merils@christcollegeijk.edu.in

Tom Cherian
Department of Chemistry
Christ College (Autonomous),
Irinjalakuda, Kerala, India
drtomcherian@gmail.com

ABSTRACT

Chitosan copper composites are a novel class of materials created by combining copper nanoparticles with chitosan, a biodegradable polymer derived from chitin. This composite synergizes the remarkable properties of both constituents, offering a wide array of potential applications. Chitosan contributes its biocompatibility, biodegradability, and versatile binding capabilities, while copper nanoparticles add antimicrobial, electrical, and catalytic properties. This composite's synthesis methods, including solution blending and in-situ reduction, are detailed, highlighting their influence on final properties. As an innovative convergence of biopolymers and nanomaterials, chitosan copper composites present a promising avenue for developing advanced materials with diverse applications.

Keywords— chitosan; biocomposite; copper coating; nano-materials

I. INTRODUCTION

Nanotechnology is the study of materials whose dimensions ranges from 1 - 100 nm, which are designed for specialized applications [1]. A composite is a multiphase material that exhibits significant amount of each constituent phase's qualities, providing better combination of properties in such a way that better property combinations are created by the careful combining of two or more unique materials [2]. Nano-composites (NC) are composite materials with nanoscale modifications in one of the phases. The definition of nano-composite material has grown substantially over the years to include a wide range of systems, including one-dimensional, two-dimensional, three-dimensional, and amorphous materials comprised of distinctly dissimilar components which are blended at the nanoscale scale. They were originally reported on 1950 followed by the studies of polyamide nanocomposites in 1976. However, they were not widely explored in both academic and industry facilities until Toyota researchers launched a systematic analysis of polymer/layered silicate clay material composites in the early 1980s and later becoming the most utilized material [3-4]. According to Azonano (2009), nanocomposites are "materials with a nanoscale structure that improve the macroscopic properties of products." He discovered that nanocomposites are often made of carbon, clay, polymer, or a mixture of these components using nanoparticle building blocks [5]. NC has gained popularity in recent years due to its superior mechanical strength, solvent resistant properties, better thermal stability as well as fire retardant qualities [6]. The particle size and distribution, surface features, geometric shape, dispersion state and the commercial accessibility of nano-particles has increased the production as well as applications of NC to a great extent [7].

1. Classification

Nanocomposites can be classified into various categories based on the materials incorporated, dimensions of the framework, types of reinforcement material, and synthetic approach. The commonly observed fillers used in nanocomposites are shown in Figure 1. They are a class of materials formed by integrating nanoparticles into a matrix, have emerged as a revolutionary area of research with diverse applications across scientific, industrial, and technological domains. The controlled manipulation of materials at the nanoscale imparts novel properties and functionalities, often surpassing those of their individual components. Among the intriguing array of nanocomposites, chitosan-copper nanocomposites stand out as a remarkable example of synergistic material engineering, combining the inherent strengths of chitosan and copper nanoparticles. This review delves into the synthesis methods, properties, and wide-ranging applications of chitosan-copper nanocomposites, underscoring their significance in various fields.




Figure 1: Fillers used for the preparation of nano-composites

2. Properties of copper and chitosan as an antimicrobial agent

The fusion of biopolymers and metals has emerged as a groundbreaking innovation with far-reaching implications across diverse industries. This convergence brings together the versatility of biopolymers, derived from renewable natural sources, and the unique properties of metal nanoparticles, often at the nanoscale, to create a new class of materials that transcends the capabilities of their individual components. The importance of biopolymer and metal composites spans numerous fields, from medicine to electronics, environmental remediation, and beyond. Biopolymers, such as chitosan, cellulose, and starch, embody sustainability. Sourced from renewable materials, they present a greener alternative to synthetic polymers. Chitosan is a natural, biodegradable, and cost-effective biopolymer. Chitosan possesses intriguing antimicrobial properties [8]. As a result, chitosan is commonly employed in antibacterial applications due to its antibacterial activities against gram-positive bacteria, gram-negative bacteria, and fungi [9]. Chitosan has piqued the interest of researchers as a nano-composite matrix due to its novel features for a variety of applications. Integrating them with metal nanoparticles, like silver, gold, copper enhances their functionalities, creating materials that are not only environmentally friendly but also biocompatible. The antibacterial capabilities of copper were used by ancient cultures long before the nineteenth century when the idea of germs was first defined. Cu has the intrinsic ability to kill germs when it comes into touch with them [10-12]. In-depth research has been done on the molecular mechanisms behind copper's antibacterial effects. Additionally, researchers are demonstrating the inherent ability of copper alloy "touch surfaces" to eliminate a variety of germs that pose a concern to public health [13]. Victor Burq conducted considerable study to support his discovery that in 1852 that those who worked with copper experienced far fewer cholera mortality than anyone else. He submitted his research to the French Academies of Science and Medicine in 1867, telling them that applying copper to the skin could help prevent cholera [14]. An extensive variety of bacteria can be eliminated by copper alloy surfaces naturally. There have been a lot of peer-reviewed antimicrobial efficacy studies on copper's ability to kill *E. coli* O157:H7, methicillin-resistant *Staphylococcus aureus* (MRSA), *Staphylococcus*, *Clostridium difficile*, influenza A virus, adenovirus, and fungi over the past ten years. These studies have been done in the interest of preserving public health, especially in healthcare settings with their susceptible patient populations [15]. A variety of studies have been conducted in this area during the past several years.

Arun et al. studied the mechanical characteristics of the electrodeposited copper thin film; deposited on double zincated aluminium, such as scratch resistance and microhardness. The size of the copper coating's crystallites was used to quantify the coating's scratch and microhardness and to correlate those values. With the decrease of crystallite size, it was discovered that both characteristic values increased. Using the colony count method, the

coated sample's antimicrobial effectiveness was assessed against Escherichia coli bacteria and compared to that of commercially available bulk copper. After six hours of exposure to the copper-coated surface, 94% of E. coli cells had died [17]. The maximum strength of nanotwinned copper samples with varying twin thicknesses was examined by Liu et al. By using the electrodeposition process, 99.99% pure copper thin film with nanocrystalline size can be easily produced on the aluminium touch surface [18]. Neo et al. effectively created a super hydrophilic surface by electrolytic plasma oxidation of aluminium (Al) followed by Cu-dotted electroplating. E. coli ATCC 25922, methicillin-resistant Staphylococcus aureus (MRSA) ATCC 43300, and vancomycin-resistant Enterococcus faecium (VRE) ATCC 51299 were all killed by the Cu plate and Cu-dotted oxide surfaces. It was discovered that the super hydrophilic Cu-dotted oxide coating surface provides an excellent technique for suppressing bacterial growth and survival on contact surfaces, lowering the danger of infection and disease spread, particularly in moist or wet conditions. [19]. Using the electrodeposition technique, a copper thin film was created on double zincated aluminium. The crystalline size has a direct impact on the coating's surface energy. Surface shape, in addition to surface energy, plays an important effect in surface wettability. The coating shape and crystallite size alter as the electrodeposition current density (j) changes [20].

By utilizing electrodeposition in a non-cyanide alkaline bath, Arun et al. effectively explored the copper coating on the aluminium surface. Before copper is deposited, the substrate has been pre-zincated to ensure strong adherence and was confirmed by Williamson-Hall method's strain energy calculation method. Additionally, studies on the wettability of double-distilled water with respect to the electrodeposited copper coatings that are coated at various current densities are conducted. The coating is more water-wettable at greater current densities because, under these circumstances, the coating's grain size is reduced, and its shape changes to a more advantageous dense nodularity [21]. In order to treat the E. coli ATCC 25922 culture with 99.99% pure copper thin film, which is created by the electrodeposition method, Arun et al. explored the mode of attack of copper ions on microorganisms. Analysis has been done on the morphological alterations and the structural changes of the cell in E. coli cells. Studies using electron microscopy showed that copper-treated E. coli cells had more wrinkling and damage than untreated ones. This is because the lesions that the copper ions cause a large number of ions and amino acids to inflow and efflux [22]. This biocompatibility is paramount in medical applications, where the potential for reduced toxicity and adverse effects makes biopolymer-metal composites ideal candidates for implants, drug delivery, wound healing and potential materials for touch surfaces. Various methods for the preparation of chitosan/copper composites are shown in Table 1.

Table 1: Applications of chitosan/copper nanocomposites

Sl no	System	Method of preparation	Applications
1	chitosan-copper nanocomposite (CS-Cu)	Synthesized without the aid of any external chemical-reducing agents.	Photocatalyst Antimicrobial agent Anticancer agent [23]
2	chitosan-based copper nanocomposite (CCNC),	mixing chitosan and copper nanoparticles.	Wound healing [24]
3	cuprous oxide/chitosan nanocomposites	electrochemical deposition	Photocatalyst for degradation of Brilliant red X-3B [25]
4	CuO/chitosan nanospheres	straightforward wet chemical procedure	Photocatalyst for destruction of organic pollutants [26]
5	Chitosan (ChdSb)/copper oxide (CuO) nanoparticles		Photocatalyst [27]
6	Cu ₂ O/crosslinked-chitosan nanocomposites (Cu ₂ O/CS NCs)	straightforward liquid phase precipitation-reduction	Photocatalyst for decolorization of dye X-3B [28]
7	Chitosan (CS) attached copper oxide (CuO)	chemical precipitation process	Photocatalyst for Methylene blue (MB) dye degradation, Antibacterial agent [29]
8	Chitosan base copper oxide (CH-CuO) nanoparticles	environmentally friendly production	Photocatalyst, Antibacterial agent [30]
10	Copper oxide nanoparticles (CS-CuO nanocomposite)	Eco-friendly production	Antibacterial agent [31]

11	Water-dispersible chitosan nanoparticles loaded with mixed valence copper	hydrothermal (HT) approach	Antibacterial agent [32]
12	Copper nanoparticles (NpCu) with chitosan matrix	Green synthesis	Antibacterial agent [33]
13	Copper-chitosan nano composites	Metal-vapor synthesis (MVS)	Antifungal agent [34]

3. Chitosan- Copper nanocomposites

Chitosan/nCu is frequently utilised to improve healing or infection control, with particular emphasis on the antibacterial mode of action and toxicity [35]. Copper nanoparticles (CCNC), was applied externally to measure its wound healing capability and to explore its effects on some essential components of the healing process.. Wound contraction was significantly increased in the CCNC-treated animals. It was discovered that chitosan-based copper nanocomposite effectively promoted cutaneous wound healing by modulating numerous cells, cytokines, and growth factors at various stages of the healing process [36]. It has been known that, adding copper to wound dressings would improve wound healing when compared to control dressings (without copper) or commercial wound dressings containing silver. This demonstrates the ability of copper based materials to promote wound healing and gives information on the molecular mechanisms by which copper oxide-impregnated dressings promote wound healing [37]. Due to these advantages they have been used in biological applications such as the production of drug-resistant antimicrobials and anticancer medicines [23]. To enhance the antibacterial capabilities and corrosion resistance of the substrate, the coating of chitosan-copper nanocomposite on stainless steel 316L using electrophoretic deposition was conducted by varying concentrations of Cu nanoparticles after the in-situ synthesis of Cu nanoparticles modified by chitosan. Several Gram-positive and Gram-negative microorganisms were used to examine the antibacterial effects of nanocomposite coatings. Results showed that the antibacterial activity and corrosion resistance of 316L stainless steel substrates were significantly improved [25]. The first eco-friendly bio-inspired chitosan/copper oxide (CS-CuO) nanocomposite utilising rutin was developed and has been developed as a potential anticancer drug [38]. The anti-bacterial efficacy of chitosan/copper nanocomposites (CS/Cu-NCs) and chitosan/polyacrylic acid/copper hydrogel nanocomposites (CS/PAA/Cu-HNCs), towards bacteria, fungus, and yeast showed that CS/PAA/Cu-HNCs had higher swelling percentage and copper release than CS/Cu-NCs [39].

Sun et al. prepared chitosan-copper-gallic acid nanocomposites (CS-Cu-GA NCs) using microwave-assisted techniques. Chitosan, Cu NPs, and Cu²⁺ all have built-in antibacterial capabilities that are combined in CS-Cu-GA NCs. The prepared systems effectively promoted the healing of wounds infected with *S. aureus* while causing no harm to healthy tissues. Additionally, a bandage with superior water swelling and antibacterial properties was created using the antimicrobial dressing [40]. The green synthesis method was an environmentally benign way to create physiologically active copper oxide nanoparticles from *Ficus carica* leaf extract. The antibacterial activity of copper nanoparticles and chitosan alone was found to be less than that of the Cu-chitosan nanoparticle composite, indicating that the antibacterial activity of CuO NPs is greatly enhanced by the addition of chitosan stabiliser [41]. The type of coating material, which is determined by the degree of improvement in the % RBC of both Gram-positive and Gram-negative bacteria, follows the following descending order: fabric coated with CuO/chitosan nanocomposite > fabric coated with chitosan nanoparticles > none. It is obvious that the higher percent RBC results refer to the treated fabric samples' enhanced antibacterial activity [42].

By using in situ reduction of Cu(II) to immobilise copper nanoparticles on the amino-enriched surface of chitosan (CTS), Miao et al. created L-ascorbic acid-stabilized Cu-CTS nanocomposites. The average size of the copper nanoparticles was 2.6 ±0.5 nm. It was discovered that the Cu-CTS nanocomposites exhibited a broad antibacterial range and high antimicrobial activity against *Monilia albican* and *S. aureus* [43]. Umoren et al. created the chitosan-copper oxide (CHT-CuO) nanocomposite using CuSO₄ .5H₂O as a precursor and olive leaf extract (OLE) as a reducing agent. By using the cup plating or disc diffusion methods, the antibacterial activity of the synthesized nanocomposites was assessed. As-Synthesized CHT-CuO nanocomposite demonstrates encouraging antimicrobial properties and may be used as an antibacterial agent in packaging and medical applications [44].

4. Chitosan-copper nanocomposite hydrogel

Copper nanoparticles were prepared through a precipitation process and a pseudonatural cationic chitosan biopolymer was used as a stabilising agent for the preparation of chitosan-copper nanocomposite hydrogel. Solution casting was used to create the nanocomposite hydrogels from the produced nanoparticles in a 1:1 blend

of chitosan and pluronic F127 polymer solution. Through an inhibition zone method, the created nanocomposite hydrogels were evaluated for their antibacterial efficacy. The findings demonstrated that the copper-embedded chitosan-pluronic F127 nanocomposite hydrogels may be utilized successfully for both wound care and antibacterial applications [45]. The studies on copper-chitosan nanocomposite-based chitosan hydrogels (Cu-Chit/NCs hydrogel) demonstrates the antifungal activity of Cu-Chit/NCs hydrogels against aflatoxigenic strains of *A. flavus* and demonstrates that, depending on the kind of fungal strain and nanocomposite concentration, the antifungal activity of nanocomposites in vitro can be successful. It was also observed that Cu-Chit/NCs hydrogel reduces the impact of G6DP isozyme without changing the activity of peroxidase isozymes [46]. By adding the Cu^{2+} ions to a hydrogel made of chitosan, Vanashi et al. created a copper-containing hydrogel (Cu/CH). For the formation of the hydroxyl radical, a catalytic mechanism was suggested. The research on reusability revealed that Cu/CH can be recycled multiple times without losing its catalytic activity. The performance of various metal ions injected into the hydrogel in the generation of hydroxyl radical was also examined [47]. Paul *et al.* concentrate on creating a topical administration system for a greenly synthesized copper oxide nanocomposite gel. In order to treat human diseases, the healthcare sector is under a lot of strain and requires unique, multifunctional materials. The most innovative materials now used in the medical field are biopolymers covered with nanocomposites. The CS-CuO nanocomposite gel that was created possesses antibacterial qualities and works well when applied topically [48].

5. Chitosan-copper beads

The possibility of chitosan – copper beads in drug delivery applications were studied by Sana *et.al.* They synthesized CuO nanoparticles in situ during the development of physically cross-linked chitosan hydrogel beads using sodium tripolyphosphate as the cross-linker. They showed good antibacterial properties against *E. coli* and *S. Aureus* [49]. Copper chitosan composites represent a promising and innovative class of materials with a wide range of potential applications. Through the synergistic combination of chitosan's biocompatibility and copper's antimicrobial properties, these composites offer unique advantages in various fields such as biomedicine, environmental remediation, and food preservation. The incorporation of copper into chitosan matrices enhances their antimicrobial efficacy, making them effective agents against a broad spectrum of pathogens. This is particularly valuable in medical applications where reducing the risk of infections is critical, as well as in water treatment systems where the removal of harmful microorganisms is essential for maintaining water quality.

II CONCLUSIONS

The versatile nature of copper chitosan composites allows for their adaptation into different forms, such as films, membranes, coatings, and nanoparticles, thereby enabling their use in diverse scenarios. Their biodegradability and reduced environmental impact compared to traditional antimicrobial agents also contribute to their attractiveness from a sustainability standpoint. However, challenges still remain in terms of optimizing the composite's properties, ensuring consistent performance, and addressing potential cytotoxicity concerns. Further research is needed to thoroughly understand the long-term stability, release kinetics, and interactions of these composites with various environments. In the coming years, as research and development in the field of materials science progress, copper chitosan composites are likely to play a pivotal role in revolutionizing multiple industries, offering innovative solutions to address microbial contamination, infection control, and environmental preservation. Continued efforts in advancing their formulation, synthesis techniques, and application methods will unlock their full potential, leading to a safer and healthier future.

ACKNOWLEDGEMENT

The authors would like to acknowledge Christ College Research SEED Fund (CCRSF) (2023-2024) provided by Christ College (Autonomous), Irinjalakuda, Thrissur, Kerala, India for providing the research and funding facilities.

REFERENCES

- [1] R. ed., Waser, *Nanotechnology: volume 4: information technology II*. John Wiley & Sons, 2008.
- [2] W.D., Jr Callister., *Materials science and engineering an introduction*, 2007.
- [3] C.C. Okpala, Nanocomposites—an overview. *International Journal of Engineering Research and Development*, 8(11), pp.17-23, 2013.
- [4] B. Briell, Nanoclays-counting on consistency. *Southern Clay Products, Inc.*, 2000.
- [5] C.C. Okpala, The benefits and applications of nanocomposites. *Int. J. Adv. Eng. Tech*, 12, p.18., 2014
- [6] I. ed. Manas-Zloczower, *Mixing and compounding of polymers: theory and practice*. Carl Hanser Verlag GmbH Co KG., 2012.
- [7] T.V. Kosmidou, A.S. Vatalis, C.G. Delides, E. Logakis, P. Pissis, and G.C. Papanicolaou, Structural, mechanical and electrical characterization of epoxy-amine/carbon black nanocomposites. *Express Polymer Letters*, 2(5), pp.364-372, 2008.

- [8] K.Wang, S. Pan, Z. Qi, P. Xia, H. Xu, W. Kong, H. Li, P. Xue, X. Yang, and C. Fu, Recent advances in chitosan-based metal nanocomposites for wound healing applications. *Advances in materials science and engineering*, 2020, pp.1-13, 2020.
- [9] A. Mohandas, S. Deepthi, R. Biswas, and R.Jayakumar, Chitosan based metallic nanocomposite scaffolds as antimicrobial wound dressings. *Bioactive materials*, 3(3), pp.267-277, 2018.
- [10] D. HHA, Historic uses of copper compounds in medicine. *Trace Elements Med*, 2, pp.80-87, 2001.
- [11] G. Borkow, and J. Gabbay, Copper, an ancient remedy returning to fight microbial, fungal and viral infections. *Current Chemical Biology*, 3(3), pp.272-278, 2009.
- [12] S.S. Siwal, Q.Zhang, A.K. Saini, and V.K.Thakur, Antimicrobial materials: new strategies to tackle various pandemics. *Journal of Renewable Materials*, 8(12), pp.1543-1563, 2020
- [13] W.H. English, Copper, 29 Cu. *History*, 7440, pp.50-8.
- [14] S. Love, Copper Destroys Viruses and Bacteria. Why Isn't It Everywhere. *VICE*, March, 18, 2020
- [15] Z.A. Avakian, and I.L.Rabotnova, On determination of copper concentrations toxic to microorganisms. *Mikrobiologiia*, 35(5), pp.805-811, 1966.
- [16] Z.A. Avakian, and I.L.Rabotnova, On determination of copper concentrations toxic to microorganisms. *Mikrobiologiia*, 35(5), pp.805-811, 1966.
- [17] A. Augustin, P. Huilgol, K.R. Udupa, and U. Bhat, Effect of current density during electrodeposition on microstructure and hardness of textured Cu coating in the application of antimicrobial Al touch surface. *Journal of the mechanical behavior of Biomedical materials*, 63, pp.352-360, 2016.
- [18] L. Lu, X. Chen, X. Huang, & K. Lu, Revealing the maximum strength in nanotwinned copper. *Science*, 323(5914), 607-610, (2009).
- [19] Y. Nie, C. Kalapos, X. Nie, M. Murphy, R. Hussein, and J. Zhang, Superhydrophilicity and antibacterial property of a Cu-dotted oxide coating surface. *Annals of Clinical Microbiology and Antimicrobials*, 9(1), pp.1-10, 2010.
- [20] A. Augustin, K.U. Bhat, K.R. Udupa, and A.C. Hegde, October. Electron microscopic study of nodules formed during electrodeposition of copper on aluminium. In *Materials Science Forum* (Vol. 830, pp. 371-374). Trans Tech Publications Ltd., 2015.
- [21] A. Augustin, K.R. Udupa, and K.U. Bhat, Effect of coating current density on the wettability of electrodeposited copper thin film on aluminum substrate. *Perspectives in Science*, 8, pp.472-474, 2016.
- [22] A. Augustin, H. Thaira, K. Udaya Bhat, and K.R. Udupa, Effect of Electrodeposited Copper Thin Film on the Morphology and Cell Death of E. Coli; an Electron Microscopic Study. *Biotechnology and Biochemical Engineering: Select Proceedings of ICACE 2015*, pp.227-232, 2016.
- [23] N. Arjunan, C.M. Singaravelu, J. Kulanthaivel, and J. Kandasamy, A potential photocatalytic, antimicrobial and anticancer activity of chitosan-copper nanocomposite. *International journal of biological macromolecules*, 104, pp.1774-1782, 2017
- [24] A. Gopal, V. Kant, A. Gopalakrishnan, S.K. Tandan, and D. Kumar, Chitosan-based copper nanocomposite accelerates healing in excision wound model in rats. *European journal of pharmacology*, 731, pp.8-19, 2014.
- [25] E.S.H.R. Tabesh, H.R. Salimijazi, M. Kharaziha, M. Mahmoudi, and M. Hejazi, Development of an in-situ chitosan-copper nanoparticle coating by electrophoretic deposition. *Surface and Coatings Technology*, 364, pp.239-247, 2019.
- [26] J.Y. Chen, P.J. Zhou, J.L. Li, and Y. Wang, Studies on the photocatalytic performance of cuprous oxide/chitosan nanocomposites activated by visible light. *Carbohydrate Polymers*, 72(1), pp.128-132, 2008.
- [27] V.S. Narayanan, P.V. Prasath, K. Ravichandran, D. Easwaramoorthy, Z. Shahnava, F. Mohammad, H.A. Al-Lohedan, S. Paiman, W.C. Oh, and S. Sagadevan, Schiff-base derived chitosan impregnated copper oxide nanoparticles: An effective photocatalyst in direct sunlight. *Materials Science in Semiconductor Processing*, 119, p.105238, 2020.
- [28] C. Cao, L. Xiao, L. Liu, H. Zhu, C. Chen, and L. Gao, Visible-light photocatalytic decolorization of reactive brilliant red X-3B on Cu₂O/crosslinked-chitosan nanocomposites prepared via one step process. *Applied Surface Science*, 271, pp.105-112, 2013.
- [29] Y. Haldorai, and J.J. Shim, Multifunctional chitosan-copper oxide hybrid material: photocatalytic and antibacterial activities. *International Journal of Photoenergy*, 2013
- [30] M.H. Sarfraz, S. Muzammil, S. Hayat, M. Khurshid, and A.H. Sayyid, Fabrication of chitosan and Trianthemaptulacastum mediated copper oxide nanoparticles: Antimicrobial potential against MDR bacteria and biological efficacy for antioxidant, antidiabetic and photocatalytic activities. *International Journal of Biological Macromolecules*, 242, p.124954, 2023.
- [31] S. Sathiyavimal, S. Vasantharaj, T. Kaliannan, and A. Pugazhendhi, Eco-biocompatibility of chitosan coated biosynthesized copper oxide nanocomposite for enhanced industrial (Azo) dye removal from aqueous solution and antibacterial properties. *Carbohydrate polymers*, 241, p.116243, 2020.
- [32] S. Basumallick, P. Rajasekaran, L. Tetard, and S. Santra, Hydrothermally derived water-dispersible mixed valence copper-chitosan nanocomposite as exceptionally potent antimicrobial agent. *Journal of nanoparticle research*, 16, pp.1-11, 2014.
- [33] D.A. Marin-Silva, N. Romano, L. Damonte, L. Giannuzzi, and A. Pinotti, Hybrid materials based on chitosan functionalized with green synthesized copper nanoparticles: Physico-chemical and antimicrobial analysis. *International Journal of Biological Macromolecules*, 242, p.124898, 2023.
- [34] M.S. Rubina, A.Y. Vasil'kov, A.V. Naumkin, E.V. Shtykova, S.S. Abramchuk, M.A. Alghuthaymi, and K.A. Abd-Elsalam, Synthesis and characterization of chitosan-copper nanocomposites and their fungicidal activity against two sclerotia-forming plant pathogenic fungi. *Journal of Nanostructure in Chemistry*, 7, pp.249-258, 2017.
- [35] M. Shi, H.S. Kwon, Z. Peng, A. Elder, and H. Yang, Effects of surface chemistry on the generation of reactive oxygen species by copper nanoparticles. *ACS nano*, 6(3), pp.2157-2164, 2012.
- [36] A. Gopal, V. Kant, A. Gopalakrishnan, S.K. Tandan, and D. Kumar, Chitosan-based copper nanocomposite accelerates healing in excision wound model in rats. *European journal of pharmacology*, 731, pp.8-19, 2014.
- [37] G. Borkow, J. Gabbay, R. Dardik, A.I. Eidelman, Y. Lavie, Y. Grunfeld, S. Ikher, M. Huszar, R.C. Zatzoff, and M. Marikovsky, Molecular mechanisms of enhanced wound healing by copper oxide-impregnated dressings. *Wound repair and regeneration*, 18(2), pp.266-275, 2010.
- [38] D. Bharathi, R. Ranjithkumar, B. Chandarshekar, and V. Bhuvaneshwari, Bio-inspired synthesis of chitosan/copper oxide nanocomposite using rutin and their anti-proliferative activity in human lung cancer cells. *International Journal of Biological Macromolecules*, 141, pp.476-483, 2019.
- [39] M.E. Abd El-Aziz, S.M.M. Morsi, D.M. Salama, M.S. Abdel-Aziz, M.S. Abd Elwahed, E.A. Shaaban, and A.M. Youssef, Preparation and characterization of chitosan/polyacrylic acid/copper nanocomposites and their impact on onion production. *International journal of biological macromolecules*, 123, pp.856-865, 2019.
- [40] X. Sun, M. Dong, Z. Guo, H. Zhang, J. Wang, P. Jia, T. Bu, Y. Liu, L. Li, and L. Wang, Multifunctional chitosan-copper-gallic acid based antibacterial nanocomposite wound dressing. *International Journal of Biological Macromolecules*, 167, pp.10-22, 2021.
- [41] S.M. Syame, W.S. Mohamed, R.K. Mahmoud, and S.T. Omara, Synthesis of copper-chitosan nanocomposites and their applications in treatment of local pathogenic isolates bacteria. *Orient J Chem*, 33(6), pp.2959-2969, 2017.

- [42] M. Gouda, and A.Hebeish, Preparation and evaluation of CuO/chitosan nanocomposite for antibacterial finishing cotton fabric. *Journal of Industrial Textiles*, 39(3), pp.203-214, 2010.
- [43] M. He, L. Lu, J. Zhang, and D.Li, Facile preparation of L-ascorbic acid-stabilized copper-chitosan nanocomposites with high stability and antimicrobial properties. *Science Bulletin*, 60(2), pp.227-234, 2015.
- [44] P.S.Umoren, D. Kavaz, A.Nzila, S.S. Sankaran, and S.A.Umoren, Biogenic synthesis and characterization of chitosan-cuo nanocomposite and evaluation of antibacterial activity against gram-positive and-negative bacteria. *Polymers*, 14(9), p.1832, 2022.
- [45] T.Jayaramudu, K. Varaprasad, K.K. Reddy, R.D.Pyarasani, A. Akbari-Fakhrabadi, and J. Amalraj, Chitosan-pluronic based Cu nanocomposite hydrogels for prototype antimicrobial applications. *International journal of biological macromolecules*, 143, pp.825-832, 2020.
- [46] K.A. Abd-Elsalam, M.A.Alghuthaymi, A.Shami, M.S.Rubina, S.S.Abramchuk, E.V. Shtykova, and A.Yu. Vasil'kov, Copper-chitosan nanocomposite hydrogels against aflatoxigenic *Aspergillus flavus* from dairy cattle feed. *Journal of Fungi*, 6(3), p.112, 2020.
- [47] A.K. Vanashi, and H. Ghasemzadeh, Copper (II) containing chitosan hydrogel as a heterogeneous Fenton-like catalyst for production of hydroxyl radical: A quantitative study. *International Journal of Biological Macromolecules*, 199, pp.348-357, 2022.
- [48] S.Paul, D. MK, and S.Peter, Development of green synthesized chitosan-coated copper oxide Nanocomposite gel for topical delivery. *Journal of Pharmaceutical Innovation*, pp.1-10, 2022.
- [49] S. Farhoudian, M. Yadollahi, and H. Namazi, Facile synthesis of antibacterial chitosan/CuO bio-nanocomposite hydrogel beads. *International journal of biological macromolecules*, 82, pp.837-843, 2016.