

Synthesis of Nanoparticles utilizing Plant Extract

Dr. Sameeran Kumar Das

Assistant Professor

Madhab Choudhury College, Barpeta, Assam, India, PIN-781301

Email ID: sameer.kr35@gmail.com

Abstract

Nanoparticles (NPs) being used most widely now-a-days, are in verge of developing new methodologies for their preparation. Focusing on the *sustainable development* goal and understanding the *Green Chemistry principles*, it is given utmost importance for synthesis of NPs utilising different plant extracts. Here in this chapter, we are discussing on synthesis NPs by utilizing plant extract by taking the example of synthesis of Pd NPs.

Key words: NPs, Green synthesis, Plant extract

Introduction

In recent days, scientific community focus on the concept of sustainable development *i.e.* development of the current necessities without hampering the needs of the future generation [1]. In this regard, methodologies developed with the acceptance of *Green Chemistry Principles* [2] is the prime goal of the researchers which can lead to the fulfilment of the concept of sustainable development. Presently, nanotechnology has become an emerging area which has immense effect on various fields. NPs have small size and they have commendable physicochemical properties which are clearly diverse from their bulk counterparts [3]. NPs have been synthesized traditionally mostly by chemical methods. Many methods are utilised for the preparation of metallic NPs under various physiological and environment friendly conditions like microwave, sonochemical, electrochemical, ionic liquids, supercritical liquids etc [4]. But most of the methodologies are confronted with the drawback of using toxic chemicals and in the process of synthesis, by-products are generated; moreover, there are some other economic issues related with the process [5]. Because of this, researchers are continuously working on developing new environment friendly, less toxic and economically viable methodologies for NP synthesis. As such, bio-based methodologies utilising different microorganisms like fungi, yeast, algae, bacteria etc, as alternative to the traditional methods, have been developed [6]. Along with these, plant extracts have been extensively explored in

recent days because they are easily available, cost effective as well as easy handling [7]. Besides, in the synthesis of NPs, it plays effective role as an efficient stabilizing or reducing agent [7]. These plant extract contain a wide range of phytochemicals, presence of which may act as stabilizing and/or reducing agents in the synthesis process of NPs [8]. Different plant components *viz.* leaves, roots, stems, fruits, and seeds are extensively utilized for the synthesis of different NPs [9]. Thus, easy to use nature along with the diversity of plants, plant extract mediated green synthesis of NPs is now considered as a commanding technique amongst various biological methods. NPs synthesized utilizing plant extracts have definite size, shape, and composition and they are less harmful to human than that of the NPs synthesized chemically [8].

Plant extract mediated synthesis of NPs


Many more literatures are found regarding the synthesis of NPs utilizing plant extracts. Plant extract means the extracts obtained from different parts of a tree *viz.* leaf, stem, fruit, root, latex, bark residue, peels of fruits and seeds [9].

Plant extracts mainly contain active ingredients like phenols, terpenoids, quinines, alkaloids, amides, alcohols, flavonoids and proteins which are mainly associated with the process of reduction of metal cations to NPs [10]. Carbonyl, hydroxyl, amine and methoxide basically found in the active ingredients of plant extracts and they are the main functional groups which react with the precursor [11]. Among these ingredients, flavonoids and phenols have the ability to act as stabilizers which prevent the aggregation of as-synthesized NPs [10].

In general, the plant extract mediated NP synthesis involves three main phases *viz.* I) reduction phase, II) growth phase and III) termination phase. A short summary of these steps is given below [12, 13].

- I) In the first phase, which is the reduction phase, the reducing phytoactives contained in the plant extract have the ability to reduce the metal ions to zero-valent metal atoms by transferring electrons.
- II) In the second phase, the zero-valent atoms produced starts growing to nanometallic particles of different shapes like triangular, linear, hexagonal, cubic or rod shaped by aggregation.
- III) In the final stage, named termination stage, the phytoactive components with antioxidant properties present in the extract help to uphold the stability of NPs by enriching themselves around the NPs.

Some of the active ingredients found in the plant extract are shown in the figure below (Fig. 1).



Plant extract in the synthesis of Pd NPs

In present day, Pd NPs, on account of their high surface area as well as high surface energy, have found immense applications in various fields like organocatalysis, in biosensors, in hydrogen production, in supercapacitors etc [14]. They exhibit excellent catalytic activities in organic transformation reactions. But the synthetic routes of Pd NPs mostly require high temperature, ultra sonication, active reducing agent etc [15], which have been trying to avoid by searching for mild, environment friendly, easy handling methodologies by the scientific community. As such, there is a continuous effort for the development of green methodologies for the synthesis of Pd NPs in one step with least quantity of chemicals utilising environmentally benign plant extracts.

Many literatures are found for the synthesis of Pd NPs utilizing different plant extracts. Some of the reported literatures are listed below in Table 1.

Table 1: Some literatures of Pd NPs synthesis utilizing plant extract	
Plant Extract	Reference
<i>Ocimum sanctum</i>	[5]
<i>Papaya peel</i>	[16]
<i>Pomegranate peel</i>	[17]
<i>Diopyros kaki. leaf</i>	[18]
<i>Banana peel</i>	[19]
<i>Cinnamom zeylanicum bark</i>	[20]
<i>C. Camphora leaf</i>	[21]
<i>Curcuma longa tuber</i>	[22]
<i>Rosa canina fruit</i>	[23]
<i>Pistacia atlantica kurdica gum</i>	[24]

<i>Pectin</i>	[25]
<i>Stachys lavandulifolia</i>	[26]
<i>Oak gum</i>	[27]
<i>Camellia sinensis leaves (black tea)</i>	[28]
<i>Ananas comosus</i> leaf extract (ACLE)	[29]
<i>Moringa oleifera</i> Leaf Extract	[30]

Extensive researches are still going on regarding the plant extract facilitated Pd NPs synthesis.

After synthesis of the Pd NPs, these are characterized by different spectroscopic and analytical methods. Pd NPs are mainly characterized by HRTEM (High Resolution Transmission Electron Microscopy) analysis. Moreover, SEM (Scanning Electron Microscopy) analysis, EDX (Energy Dispersive X-ray) analysis, UV-Visible spectroscopy, FTIR (Fourier Transform Infrared) spectroscopy, PXRD (Powder X-ray Diffraction) analysis, SAED (Selected Area Electron Diffraction) analysis, XPS (X-ray Photoelectron Spectroscopy) analysis etc.

Conclusion

Green Chemistry has led to the advancement of new environmentally benign methodologies for the synthesis of NPs. In this regard, it is seen that, the plant extract has a commendable impact on their synthesis due to the presence of different active biomolecules. Utilisation of plant extract retards the use of toxic chemicals required for the synthesis of the NPs and makes the process easy handling as well as economic. Moreover, the NPs synthesized by bio-routes have very good use in medical field. As such, the effective utilization of plant extract for the synthesis of NPs, has become a very good alternative pathway.

References

- [1] Robert, K. W., Parris, T. M., & Leiserowitz, A. A. (2005). What is sustainable development? Goals, indicators, values, and practice. *Environment: science and policy for sustainable development*, 47(3), 8-21.
- [2] Clark, J. H., & Macquarrie, D. J. (Eds.). (2008). *Handbook of green chemistry and technology*. John Wiley & Sons.

- [3] Sau, T. K., Rogach, A. L., Jäckel, F., Klar, T. A., & Feldmann, J. (2010). Properties and applications of colloidal nonspherical noble metal nanoparticles. *Advanced Materials*, 22(16), 1805-1825.
- [4] Khan, M., Albalawi, G. H., Shaik, M. R., Khan, M., Adil, S. F., Kuniyil, M., Alkathlan, H. Z., Al-Warthan, A. & Siddiqui, M. R. H. (2017). Miswak mediated green synthesized palladium nanoparticles as effective catalysts for the Suzuki coupling reactions in aqueous media. *Journal of Saudi Chemical Society*, 21(4), 450-457.
- [5] Sarmah, M., Neog, A. B., Boruah, P. K., Das, M. R., Bharali, P., & Bora, U. (2019). Effect of substrates on catalytic activity of biogenic palladium nanoparticles in C–C cross-coupling reactions. *ACS omega*, 4(2), 3329-3340.
- [6] Das, S. K., Laskar, K., Konwar, D., Sahoo, A., Saikia, B. K., & Bora, U. (2020). Repurposing fallen leaves to bio-based reaction medium for hydration, hydroxylation, carbon-carbon and carbon-nitrogen bond formation reactions. *Sustainable Chemistry and Pharmacy*, 15, 100225.
- [7] (a) Sivamaruthi, B. S., Ramkumar, V. S., Archunan, G., Chaiyasut, C., & Suganthy, N. (2019). Biogenic synthesis of silver palladium bimetallic nanoparticles from fruit extract of *Terminalia chebula*–In vitro evaluation of anticancer and antimicrobial activity. *Journal of Drug Delivery Science and Technology*, 51, 139-151. (b) Akhtar, M. S., Panwar, J., & Yun, Y. S. (2013). Biogenic synthesis of metallic nanoparticles by plant extracts. *ACS Sustainable Chemistry & Engineering*, 1(6), 591-602. (c) Vishnukumar, P., Vivekanandhan, S., & Muthuramkumar, S. (2017). Plant-Mediated Biogenic Synthesis of Palladium Nanoparticles: Recent Trends and Emerging Opportunities. *ChemBioEng Reviews*, 4(1), 18-36.
- [8] Hano, C., & Abbasi, B. H. (2021). Plant-based green synthesis of nanoparticles: Production, characterization and applications. *Biomolecules*, 12(1), 31.
- [9] Narayanan, K. B., & Sakthivel, N. (2011). Green synthesis of biogenic metal nanoparticles by terrestrial and aquatic phototrophic and heterotrophic eukaryotes and biocompatible agents. *Advances in colloid and interface science*, 169(2), 59-79.
- [10] Naseer, A., Ali, A., Ali, S., Mahmood, A., Kusuma, H. S., Nazir, A., Yaseen, M., Khan, M. I., Ghaffar, A., Abbas, M. & Iqbal, M. (2020). Biogenic and eco-benign synthesis of platinum nanoparticles (Pt NPs) using plants aqueous extracts and biological derivatives: environmental, biological and catalytic applications. *Journal of Materials Research and Technology*, 9(4), 9093-9107.

- [11] Benelli, G. (2016). Plant-mediated biosynthesis of nanoparticles as an emerging tool against mosquitoes of medical and veterinary importance: a review. *Parasitology research*, 115(1), 23-34.
- [12] Nasrollahzadeh, M., Ghorbannezhad, F., Issaabadi, Z., & Sajadi, S. M. (2019). Recent developments in the biosynthesis of Cu-based recyclable nanocatalysts using plant extracts and their application in the chemical reactions. *The Chemical Record*, 19(2-3), 601-643.
- [13] Dinesh, G. K., Pramod, M., & Chakma, S. (2020). Sonochemical synthesis of amphoteric Cu⁰-Nanoparticles using Hibiscus rosa-sinensis extract and their applications for degradation of 5-fluorouracil and lovastatin drugs. *Journal of Hazardous Materials*, 399, 123035.
- [14] (a) Zeng, Q., Cheng, J. S., Liu, X. F., Bai, H. T., & Jiang, J. H. (2011). Palladium nanoparticle/chitosan-grafted graphene nanocomposites for construction of a glucose biosensor. *Biosensors and Bioelectronics*, 26(8), 3456-3463. (b) Gobal, F., & Faraji, M. (2013). Electrodeposited polyaniline on Pd-loaded TiO₂ nanotubes as active material for electrochemical supercapacitor. *Journal of Electroanalytical Chemistry*, 691, 51-56.
- [15] (a) Kim, S. W., Park, J., Jang, Y., Chung, Y., Hwang, S., Hyeon, T., & Kim, Y. W. (2003). Synthesis of monodisperse palladium nanoparticles. *Nano Letters*, 3(9), 1289-1291. (b) Zhang, Z., Zha, Z., Gan, C., Pan, C., Zhou, Y., Wang, Z., & Zhou, M. M. (2006). Catalysis and regioselectivity of the aqueous Heck reaction by Pd(0) nanoparticles under ultrasonic irradiation. *The Journal of Organic Chemistry*, 71(11), 4339-4342. (c) Cano, M., Benito, A. M., Urriolabeitia, E. P., Arenal, R., & Maser, W. K. (2013). Reduced graphene oxide: firm support for catalytically active palladium nanoparticles and game changer in selective hydrogenation reactions. *Nanoscale*, 5(21), 10189-10193.
- [16] Dewan, A., Sarmah, M., Thakur, A. J., Bharali, P., & Bora, U. (2018). Greener biogenic approach for the synthesis of palladium nanoparticles using papaya peel: An eco-friendly catalyst for C–C coupling reaction. *ACS omega*, 3(5), 5327-5335.
- [17] Das, S. K., Dewan, A., Deka, P., Saikia, R., Thakuria, S., Deka, R. C., Thakur, A. J. & Bora, U. (2022). Biogenic palladium nanostructures for Suzuki-Miyaura and Sonogashira cross-coupling reaction under mild reaction conditions. *Current Research in Green and Sustainable Chemistry*, 5, 100301.
- [18] Song, J. Y., Kwon, E. Y., & Kim, B. S. (2010). Biological synthesis of platinum nanoparticles using Diopyros kaki leaf extract. *Bioprocess and biosystems engineering*, 33, 159-164.

- [19] Bankar, A., Joshi, B., Kumar, A. R., & Zinjarde, S. (2010). Banana peel extract mediated novel route for the synthesis of palladium nanoparticles. *Materials Letters*, *64*(18), 1951-1953.
- [20] Sathishkumar, M., Sneha, K., Kwak, I. S., Mao, J., Tripathy, S. J., & Yun, Y. S. (2009). Phyto-crystallization of palladium through reduction process using *Cinnamom zeylanicum* bark extract. *Journal of Hazardous materials*, *171*(1-3), 400-404.
- [21] Yang, X., Li, Q., Wang, H., Huang, J., Lin, L., Wang, W., Sun, D., Su, Y., Opiyo, J.B., Hong, L., Wang, Y., He, N. & Jia, L. (2010). Green synthesis of palladium nanoparticles using broth of *Cinnamomum camphora* leaf. *Journal of Nanoparticle Research*, *12*, 1589-1598.
- [22] Sathishkumar, M., Sneha, K., & Yun, Y. S. (2009). Palladium nanocrystal synthesis using *Curcuma longa* tuber extract. *Int J Mater Sci*, *4*(1), 11-17.
- [23] Veisi, H., Rashtiani, A., & Barjasteh, V. (2016). Biosynthesis of palladium nanoparticles using *Rosa canina* fruit extract and their use as a heterogeneous and recyclable catalyst for Suzuki–Miyaura coupling reactions in water. *Applied Organometallic Chemistry*, *30*(4), 231-235.
- [24] Veisi, H., Faraji, A. R., Hemmati, S., & Gil, A. (2015). Green synthesis of palladium nanoparticles using *Pistacia atlantica kurdica* gum and their catalytic performance in Mizoroki–Heck and Suzuki–Miyaura coupling reactions in aqueous solutions. *Applied Organometallic Chemistry*, *29*(8), 517-523.
- [25] Khazaei, A., Rahmati, S., Hekmatian, Z., & Saeednia, S. (2013). A green approach for the synthesis of palladium nanoparticles supported on pectin: Application as a catalyst for solvent-free Mizoroki–Heck reaction. *Journal of Molecular Catalysis A: Chemical*, *372*, 160-166.
- [26] Veisi, H., Ghorbani-Vaghei, R., Hemmati, S., Aliani, M. H., & Ozturk, T. (2015). Green and effective route for the synthesis of monodispersed palladium nanoparticles using herbal tea extract (*Stachys lavandulifolia*) as reductant, stabilizer and capping agent, and their application as homogeneous and reusable catalyst in Suzuki coupling reactions in water. *Applied Organometallic Chemistry*, *29*(1), 26-32.
- [27] Veisi, H., Nasrabadi, N. H., & Mohammadi, P. (2016). Biosynthesis of palladium nanoparticles as a heterogeneous and reusable nanocatalyst for reduction of nitroarenes and Suzuki coupling reactions. *Applied Organometallic Chemistry*, *30*(11), 890-896.
- [28] Lebaschi, S., Hekmati, M., & Veisi, H. (2017). Green synthesis of palladium nanoparticles mediated by black tea leaves (*Camellia sinensis*) extract: Catalytic activity in the

reduction of 4-nitrophenol and Suzuki-Miyaura coupling reaction under ligand-free conditions. *Journal of Colloid and Interface Science*, 485, 223-231.

[29] Olajire, A. A., & Mohammed, A. A. (2019). Green synthesis of palladium nanoparticles using *Ananas comosus* leaf extract for solid-phase photocatalytic degradation of low density polyethylene film. *Journal of Environmental Chemical Engineering*, 7(4), 103270.

[30] Manjare, S. B., Pendhari, P. D., Badade, S. M., Thopate, S. R., & Thopate, M. S. (2022). Biosynthesis of palladium nanoparticles from *Moringa oleifera* leaf extract supported on activated bentonite clay and its efficacy towards Suzuki–Miyaura coupling and oxidation reaction. *BioNanoScience*, 12(3), 785-794.