

# **Near Infrared Spectroscopy (NIRS): A Non-Invasive technique for evaluating the mechanics of wood material**

**Dr.Aasheesh Raturi**

**Department of Physics, Dolphin PG Institute of Biomedical and Natural Sciences, Dehradun, Uttarakhand 248007-INDIA**

**Email: Quark6ashu@gmail.com**

## **1. Introduction:**

Wood is a very important natural renewable resource; which is mostly derived from our age-less or everlasting forests. It is predominantly composed of cellulose, lignin, hemicelluloses, and minor amounts of extraneous materials (Izzekor and Fuwape 2010). The wood material can be heavy or light, stiff or flexible, and hard or soft depending on variations in the properties and volume of these components as well as variances in cellular structure. It's a common occurrence in daily life and is employed in the production of wood-frame homes, furniture, railroad ties, fence posts, utility poles, fuel wood, textile fabrics, paper, and organic chemicals.

Unlike other materials, it is an orthotropic and anisotropic material. It has different and independent mechanical properties in the direction of three mutually perpendicular axes because of the orientation of the wood fibers and the manner in which a tree increases in diameter as it grows (Amtzen and Charles 1994, Bergman et al. 2010). It can alternatively be described as a natural composite material made of hemicelluloses and lignin, with cellulose fibers serving as the reinforcing components. Mechanical properties of wood material vary along three mutually perpendicular axes: radial, tangential, longitudinal. The radial axis is perpendicular to the grain direction and normal to the growth rings, the tangential axis is perpendicular to the grain direction and tangent to the growth rings whereas the longitudinal axis is parallel to the direction of the fiber (or grain).

Although most wood properties vary along each of these three axes, variations along the radial and tangential axes are rather insignificant compared to variations along the radial or tangential axis and the longitudinal axis (Amtzen and Charles 1994). Additionally, it has a remarkable strength-to-weight ratio, and desirable building material with a sustainable utility.

The use of wood material for various end uses requires knowledge of the mechanical properties and the uniqueness that wood has in comparison with other materials used for structural purposes such as steel, iron concrete, bricks, and stone. The present chapter deals with the evaluation of mechanical properties, More specifically, modulus of elasticity (MOE), and modulus of rupture (MOR) of wood samples.

## **2. Mechanical Properties of Wood Material**

The characteristics of a material in reaction to external forces are known as its mechanical properties. According to Amtzen and Charles (1994), an external force is any force that originates from outside of a specific piece of material and has a tendency to cause the material to physically deform.

Wood's mechanical strength depends on the three polymers (cellulose, hemicellulose, and lignin) that make up the material (Kollmann and Cote 1968). The mechanical properties of the three polymers, which each significantly contribute to wood strength, are very distinct from one another. When determining the mechanical properties of wood material, consideration is given to its stiffness or elasticity, tensile strength, compressive or crushing strength, shear strength, toughness, hardness, cleavability, and resilience.

The mechanical properties of wood, such as its modulus of elasticity (MOE) and modulus of rupture (MOR), play a significant role in the performance of solid wood materials and have a significant impact on their end-use potential, which is mostly determined by variations in the structural properties of wood.

## **3. Non-Invasive Estimation of Wood Properties**

Evaluation of the mechanical properties of wood is obtained mainly through destructive methods of experimentation as per relevant standards (Pellerin and Ross 2002). In India, most of the testing is done as per Indian standards which are mostly derived from British and ASTM standards. Different countries have different standards (Rajput et al. 1991). However researchers around the world are working on indirect methods to evaluate timber properties (Tanasoïu et al. 2002, Schimleck 2008, Mora and Schimleck 2009).

Non-invasive or nondestructive testing (NDT) is a method of testing that can assess mechanical properties and detect defects in a piece of wood specimen without affecting its end-use capabilities and then using this information to make decisions regarding appropriate applications of wood material (Pellerin and Ross 2002, Tanasoïu et al. 2002). A number of NDT techniques, such as ultrasonic stress wave, deflection method, electrical method, gamma radiation method or isotope method, penetration radar method, and X-ray method used in the forest products industry, can be used to monitor and assess the quality and properties of wood and wood structures (Pellerin and Ross 2002; Tanasoïu et al. 2002).

Near-infrared (NIR) technology has received considerable attention for its use in quality control and assessing wood quality and the technical review of the technology and its potential applications in wood products is summarized by So et al.(2004). The distinctive advantages of NIR over other NDT techniques are its ability to do simultaneous analysis of many parameters (Schimleck et al. 2006b, Schimleck et al. 2007, Schimleck 2008, Mora and Schimleck 2009). The other distinctive feature is its applicability to online monitoring in the industry. In fields, the portable NIR instrument and lab-based analysis make it an important tool. Easy calibration method transfer from one machine to another machine makes it a versatile tool (Meder et al. 2003, Brashaw et al. 2009).

#### **4. Spectroscopic background of Near-Infra Red (NIR) technique**

Near Infrared Spectroscopy (NIR) has a long history that dates back to Herschel in the 1800 century. He found the light radiation beyond the visible spectrum (Barton 2002). The expansion of NIR spectroscopy has begun after 1950s from the agriculture realm into pharmaceutical, industrial processing, and imaging spectroscopy.

The NIR region with wavelength range from 800nm to 2500 nm (4000 to 12500  $\text{cm}^{-1}$ ) in which absorption bands correspond mainly to overtones and combinations of fundamental vibrations (Siesler 2006). NIR technology, which uses electromagnetic waves with transmitted or reflected spectra between 800 and 2500 nm (4000 and 12500  $\text{cm}^{-1}$ ), has primarily been utilised for nondestructive testing of organic materials including foods and agricultural products. However, it exhibits excellent potential in all areas of material assessment (for instance, polymer, textile, pharmacy, petrochemical, etc.).

#### **5. NIR Spectroscopic Assessment of mechanical properties of wood material**

Generally, the mechanical property is estimated through destructive experimentation with the help of mechanical testing machines in the laboratory. Hoffmeyer and Pedersen (1995) used near-infrared spectroscopy for the first time to offer a technology for non-destructive mechanical testing of wood that is completely distinct from standard methods (Tsuchikawa 2007). Several researchers have reported that the NIR spectroscopy can be used as nondestructive techniques for determining mechanical properties of solid wood (Kelley et al. 2004a, 2004b, Tsuchikawa et al. 2005, Fujimoto et al. 2007, 2008, Schimleck et al. 2007, Mora et al. 2008, Kothiyal and Raturi 2011).

The use of Near Infrared Spectroscopy (NIR) as non-invasive tool to evaluate specific mechanical properties, such as the modulus of elasticity (MOE), and modulus of rupture (MOR) in bending tests have been also demonstrated by a number of researchers (Mora et al. 2008, Schimleck, 2008, Schimleck et al. 2009, Hein et al. 2009, Mora and Schimleck 2010, Kothiyal and Raturi 2011).

Further, in the continuation of mechanical properties estimation by NIR spectroscopy, Kothiyal and Raturi (2011) tried to short out the problem, regarding the limitation of NIR spectroscopy application with variation in moisture content of wood in timber yards. They obtained NIR models for predicting MOR, and MOE. According to McClellan et al. (1991), lignin and cellulose absorb light at particular wavelengths, which allows NIR spectra to calculate the modulus of elasticity (MOE) and modulus of rupture (MOR) of materials.

## **6. Chemo-metrics and multivariate model development using NIR technique**

Chemo-metrics is a method of measurement and analysis based on the concept of indirect observation. The value of property of interest is deduced from measurements of a substance's chemical composition using a mathematical relationship (Lavine 1998). It aids NIR devices in resolving large, heavily overlapped peaks with high sensitivity to sample physical properties. In order to obtain the most pertinent information from the analytical data, Chemo-metrics must be used for NIR spectroscopic model development (Massart et al. 1988).

Through the use of various multivariate analysis techniques, it is possible to relate different analytical variables (such as those found in an NIR spectrum) to measure properties and extract the analytical information present in NIR spectra. With the help of the most appropriate multivariate techniques, samples with similar traits can be grouped together in order to create classifications and identify some attributes of unidentified samples for qualitative and quantitative analysis, respectively (Blanco and Villarroya 2002).

Without chemo-metric and multivariate methods, NIRS applications would not be possible. The chemo-metric technique covered the calibration by multiple linear regression (MLR), choosing a training set, spectral pre-treatments, tuning and validation, principal component analysis (PCA), quantitative calibration using partial least squares (PLS), principal component regression (PCR), qualitative calibration using discriminate analysis and regression methods for developing the calibration models as their use in the modeling process, those are included in all chemo-metric software packages.

Numerous multivariate analysis techniques can be categorised based on their objectives and computing approaches. The chosen approach depends on the analysis's objectives, the specific characteristics of the samples, and the degree of complexity of the system under evaluation (such as its nonlinearity). Once models have been developed, it is necessary to test their prediction ability using independent sets of samples that experienced the same spectral pretreatments and spectrum recording conditions as those used for calibration but were not included in the calibration regression model. The most frequently used multivariate-regression techniques in NIR spectroscopy, such as partial least squares (PLS), principal component regression (PCR), and multiple linear regression (MLR), are the best techniques for calibrating the relationship between the properties to be measured and the absorbance of NIR spectra (Agelet and Hurburgh, 2010).

Both principal component regression (PCR) and partial least-squares (PLS) regression can be applied to the entire spectrum or to specific spectral regions, and they both enable the calibration model to incorporate additional information. While PLS determines the directions of greatest variability by taking into account both spectral and target-property information, the new axes are referred to as PLS components or PLS factors, and PCR uses the principal components obtained by PCA to perform regression on the specimen property to be predicted (Martens and Naes 1991). Multiple linear regression (MLR) combines a number of spectral regions, or X-variables, in linear combinations that have a relationship as closely related to a single response (material property), or Y-vector, as possible.

The most prominent models in the field of wood material research are PLS and PCR, and both are capable of resolving significant multi-co linearity issues (Via et al. 2003). Before developing the NIR calibration model, mathematical pre-treatment of the NIR spectra is essential to enhancing signal quality and reducing noise.

Further, The two categories of pre-processing methods that are widely used are spectral derivatives and scatter-correction approaches. Multiplicative Scatter Correction (MSC), Standard Normal Variate (SNV), and Normalisation are the three fundamental preprocessing ideas used in the scatter-corrective preprocessing method. The first derivative and the second derivative are two fundamental preprocessing ideas included in the spectral derivative. Broad calibration sets may be required for heterogeneous material (like wood) than for homogeneous material. In order to account for the widest possible diversity in the calibration set, several researchers have collected more than 100 wood samples (Fujimoto et al. 2008, Hein et al. 2009, 2010).

For each regression, calibration and validation statistics include coefficient of determination ( $R^2$ ), root mean standard error of calibration (RMSEC), root mean standard error of cross-validation (RMSECV), and root mean standard error of prediction (RMSEP). The ratio of performance of deviation or relative predictive determinant (RPD), and range error ratio (RER), are the two final statistics to be discussed.

The coefficient of determination  $R^2$  can be utilized in relation to statistical models whose primary objective is the forecasting of future results based on additional pertinent information. According to Steel and Torrie (1960), this is the proportion of a data set's variability that the statistical model can explain. It gives an indication of how precisely the mathematical model is likely to anticipate future outcomes.

The root mean squared difference between the forecasts and the reference data is used for calculating the RMSEP value. It is essential to stress that this approach only works when the reference value noise is insignificant compared to the actual forecast uncertainty. Prediction errors are defined with respect to true quantities rather than noisy reference values. An absence of noisy reference values is the ideal condition for the perfect model. Of course, this limit is impractical, however (Difoggio 1995, Coates 2002) demonstrated how adding noise to the reference values can always get close to the ideal model. It should be obvious that the forecasts are accurate, and the measurement error in the reference values is the only factor that might contribute to RMSEP. In this extreme scenario, RMSEP would merely estimate the standard deviation (square root of the variance) of the measurement error of the reference value. It wouldn't be significant to the real prediction uncertainty.

The description of RMSECV is the same as RMSEP. The difference between statistical values of these parameters is used as a method for figuring out the best number of independent variables to use in building a calibration equation and based on a repetitive algorithm that selects samples from a sample set population to develop predictive model and then predicts on the remaining unselected samples (Difoggio 1995, Coates 2002).

The ratio of performance to deviation (RPD: ratio of the SD of the reference results to RMSEP) is also a appropriate statistical measurement of the ability of a NIR spectroscopy model to predict a wood properties. If RMSEP is not presented compared to the SD of the original reference data, it may be deceptive. The calibration is essentially predicting the population mean if  $RMSEP = SD$  (Bailleres et al. 2002). Prior to the introduction of RPD,


RER was used in NIR. The range of the reference values in the validation set is used for statistics, rather than standard deviation, making it comparable to RPD. Additionally, it lacks dimensions and is not dependent on any particular application (Fearn, 2002).

These are related to the capability of the model to predict future data with respect to the initial variability of the calibration data. Davies and Fearn (2006) reported the definition and application of all these terms. In the absence of a sufficient number of samples where a separate set of samples for prediction are not available other criteria are generally used (Derkyi et al. 2011) to assess the quality of a model including the root mean squares error of estimation (RMSEE), root mean square error of cross-validation (RMSECV) and the correlation coefficient of determination ( $R^2$ ). An effective model should have a modest difference between RMSEC and RMSECV, low RMSEE, low RMSECV, and high  $R^2$  between the predicted and observed values. For quantitative prediction, the correlation coefficient of determination ( $R^2$ ), which is the most popular, should be higher than 0.8. The RMSEE to SD ratio should be less than 0.2 for superior models, where SD is the standard deviation of the reference values. The SD to RMSECV ratio should be  $> 2$ , RMSECV to RMSEE  $< 1.2$ , and the SD to RMSECV ratio should be  $> 2.5$ . RMSECV can be utilized to determine how effectively an equation predicts samples that weren't used to develop the calibration equation when there aren't enough external validation samples.

Numerous researchers employed various pre-processing and statistical techniques to create superior calibration and validation models for mechanical properties of wood materials. Thumm and Meder (2001) demonstrated the use of spectra pretreatment, using first and second derivatives, and achieved a prediction coefficient of determinations ( $R^2$ ) of 0.55 to 0.72 for stiffness in the bending test. Schimleck et al. (2001a) also used the first and second derivatives to help develop PLS models that provided prediction  $R^2$  over 0.80 for both MOR and MOE. Modulus of elasticity (MOE), modulus of rupture (MOR) wood species have been accurately predicted by the number of researchers (Hoffmeyer and Pederson 1995, Gindl et al. 2001, Schimleck 2001a, Thumm and Meder 2001, Kelley et al. 2004a, 2004b, Tsuchikawa et al. 2005, Fujimoto et al. 2008, Viana et al. 2009, Kothiyal and Raturi 2011). They used NIR and various statistical techniques (PLS, MLR, and PCR) and also found that the calibration model of green wood samples can be improved by using spectral pre-processing techniques. Figure 1. illustrates the flow diagram of NIR model development and model evaluation for the mechanical properties of wood

Despite recent research demonstrating NIR's potential as a non-destructive measure of wood strength, the wood based industry has not yet adopted it. The high cost of advance NIR spectrophotometers may be the cause of this issue. However, NIR spectrophotometers with reduced spectral range are more affordable, have also been able to precisely predicted MOE and MOR. Acceptable findings were obtained with reduced ranges between 400nm and 1100 nm (Kelley et al. 2004a). Further research involving NIR spectroscopy and chemo-metric model development has produced best results and the strategy is promising for adaptation of spectral techniques to the production environment of wood based industries (Thumm and Meder 2001). The introduction of NIRS in the field of wood material science is a welcome step as more and more materials will be required for evaluation at low cost, high speed, and with improved accuracy in a non-invasive manner.

**Figure 1. Flow diagram of NIR development and models Development**



## References :

1. Agelet LE, Hurburgh CR (2010) A tutorial on near infrared spectroscopy and its calibration. *Critical reviews in Analytical Chemistry*. 40(4): 246-260.
2. Amtzen SE, Charles J (1994) *Encyclopedia of agriculture science*. Orlando, FL Academic Press. 4: 549- 561. *Appl. Spectrosc. Rev.* 42: 43-71.
3. Bailleres H, Davrieux F, Pichavant FH (2002) Near infrared analysis as a tool for rapid screening of some major wood characteristics in a eucalyptus breeding program. *Ann. For. Sci.* 59: 479–490.
4. Barton FE (2002) Theory and principles of near infra red spectroscopy. *Spectroscopy Europe*. 14 (1): 481-489.
5. Bergman R, Zhiyong C, Charlie G, Clausen CA, Dietenberger MA, Falk RH, Frihart CR, Glass SV, Hunt CG, Ibach RE, Kretschmann DE, Rammer DR, Ross RJ (2010) Forest products laboratory. Wood handbook - Wood as an engineering material. General Technical Report FPL-GTR-190. Madison, WI: U.S. Department of Agriculture Forest service, Forest products Laboratory: pp 508.
6. Blanco M, Villarroya I (2002) NIR spectroscopy: a rapid response analytical tool.
7. Coates DB (2002) Is near infrared spectroscopy only as good as the laboratory reference values An empirical approach, *Spectroscopy Europe*. 14: 24–26.
8. Davies A, Fearn T (2006) Back to basics: calibration statistics. *Spectroscopy Europe*. 18 (2): 31-32
9. Difoggio R (1995) Examination of some misconceptions about near-infrared analysis, *Appl. Spectrosc.* 49: 67–75.
10. Fearn T (2002) Assessing calibrations, chemometric space, *NIR news* 13(6): 12-14.
11. Fujimoto T, Kurata Y, Matsumoto K, Tsuchikawa S (2008) Application of near infrared spectroscopy for estimating wood mechanical properties of small clear and full length lumber specimens. *J. Infrared Spectrosc.* 16: 529-537.
12. Fujimoto T, Yamamoto H, Tsuchikawa S (2007). Estimation of wood stiffness and strength properties of hybrid larch by near-infrared spectroscopy. *Appl Spectrosc.* 61(8): 882-888
13. Gindl W, Teischinger A, Schwanninger M, Hinterstoisser B (2001) The relationship between near infrared spectra of radial wood surfaces and wood mechanical properties. *J. Infrared Spectrosc.* 9: 255–261.
14. Hein PRG, Campos ACM, Trugilho PF, Limba JT, Chaix G (2009) Near infrared spectroscopy for estimating wood basic density in *Eucalyptus urophylla* and *Eucalyptus grandis*. *Cerne Lavras*. 15(2): 133-141.
15. Hoffmeyer P, Pedersen JG (1995) Evaluation of density and strength of Norway spruce wood by near infrared reflectance spectroscopy. *Holz Als Roh-Und Werkstoff*. 53 (1): 165–170.
16. Izzekor DN, Fuwape JA (2010) Variations in mechanical properties among trees of the same and different age classes of teak (*Tectona grandis* L.F) wood. *Journal of applied sciences research*. 6(4): 562-567.
17. Kelley SS, Rials TG, Groom LR, So CL (2004a) Use of near infrared spectroscopy to predict the mechanical properties of six softwoods. *Holzforschung*. 58(3): 252– 260.
18. Kelley SS, Rials TG, Snell R, Groom LH, Sluiter A (2004b) Use of near infrared spectroscopy to measure the chemical and mechanical properties of solid wood. *Wood Sci. Technol.* 38(4): 257–276.
19. Kollmann FF, Cote WA (1968) Principles of wood science and technology. Vol. I: Solid Wood.
20. Kothiyal V, Raturi A (2011) Estimating mechanical properties and specific gravity for five year old *Eucalyptus tereticornis* having broad moisture content range by NIR spectroscopy. *Holzforschung*. 65(5): 757-762.
21. Kretschmann DE (2010) Mechanical properties of wood, 5-44: In wood handbook— wood as an engineering material. General technical report FPL-GTR-190. Madison, WI: U.S. Department of agriculture, forest service, forest products laboratory. pp 508.
22. Martens H, Naes T (1991) *Multivariate Calibration*. John Wiley, New York, USA.
23. Massart DL, Vandeginste BGM, Deming SN, Michotte Y, Kaufmann L, (1988) *Chemometrics: A Textbook*, Elsevier, Amsterdam.
24. McLellan TM, Aber JD, Martin ME, Melillo JM, Nadelhoffer KJ (1991) Determination of nitrogen, lignin, and cellulose content of decomposing leaf material by near infrared reflectance spectroscopy. *Can. J. For. Res.* 21(11): 1684- 1688.
25. Mora CR, Schimleck LR (2010) Kernel regression methods for the prediction of wood properties of *Pinus taeda* using near infrared spectroscopy. *Wood Sci. Technol.* 44:561-578.
26. Mora CR, Schimleck LR, Isik F (2008) Near infrared calibration models for the estimation of wood density in *Pinus taeda* using repeated sample measurements. *J. Near Infrared Spectrosc.* 16: 517-528.
27. Pellerin RF, Ross RJ (2002) Characteristics of wood fundamental hypothesis and static bending nondestructive evaluation methods, 3-12: In: *Nondestructive evaluation of wood*, Pellerin RF and Ross RJ, forest products laboratory, Madison, WI; Washington state university, Pullman WA.
28. Rajput SS, Shukla NK, Gupta VK, Jain JD (1991) *Timber Mechanics : strength, classification and grading of timber*. Indian council of forestry research and education, new forest Dehradun. 1-182.
29. Schimleck LR (2008) Near infrared spectroscopy: A rapid, non-destructive method for measuring wood properties and its application to tree breeding. *N. Z. J. For. Sci.* 38(1): 14-35.
30. Schimleck LR, Tyson JA, Jones PD, Peter GF, Daniels RF, Clark III A (2007) *Pinus taeda* L. wood property calibrations based on variable numbers of near infrared spectra per core and cores per plantation. *J. Near Infrared Spectrosc.* 15: 261-268
31. Siesler HW (2006) Basic principles of vibrational spectroscopy, 3-10: In *Near – infrared spectroscopy, Principles, Instruments, Application*. Wiley-VCH Verlag GmbH, D-69469 Weinheim (Germany).

32. So CL, Via B, Groom L, Schimleck L, Shupe T, Kelley S, Rials S (2004) Near infrared spectroscopy in the forest products industry. *Forest Products J.* 54(3): 6- 16.
33. Steel RGD and Torrie JH (1960) *Principles and Procedures of Statistics*, New York: McGraw-Hill, pp. 187-287.
34. Tanasoiu V, Micleaa C, Tanasoiu C (2002) Nondestructive testing techniques and piezoelectric ultrasonic transducers for wood and built in wooden structures, *Journal of optoelectronics and advanced materials.* 4 (4): 949-957.
35. Thumm A, Meder R (2001) Stiffness prediction of *Radiata pine* clear wood test species using near infrared spectroscopy. *J. Near Infrared Spectrosc.* 9:117-122
36. Tsuchikawa S (2007) A review of recent near infrared research for wood and paper. *Trends in analytical chemistry.* 21(4): 240-250.
37. Tsuchikawa S, Hirashima Y, Sasaki Y, Ando K (2005) Near infrared spectroscopic study of the physical and mechanical properties of wood with meso and microscale anatomical observation. *Appl. Spectrosc.* 59 (1): 86-93.
38. Via BK, Shupe TF, Groom LH, Stine M & So CL (2003) Multivariate modeling of density, strength and stiffness from near infrared spectra for mature, juvenile and pith wood of longleaf pine (*Pinus palustris*). *J. Near Infrared Spectrosc.* 11(5): 365–378.

\*\*\*\*\*